



A-125 Metal Roof Primer

Rust Inhibitive Primer



PRODUCT DATA SHEET

DESCRIPTION

A-125 Metal Roof Primer is a rust inhibitive primer manufactured with a dark yellow color to easily determine coverage. A-125 is designed to inhibit oxidation which results in rust degradation and to prevent bleed-through when using elastomeric coatings.

USES

A-125 Metal Roof Primer is intended for the preparation of rusty metal surfaces prior to the application of acrylic and silicone roof coatings. It is formulated to a relatively thin viscosity allowing for complete penetration and encapsulation of surface rust. Not to be used on surfaces that pond water.

COLOR

Dark yellow.

PACKAGING

Container sizes: 4.75-gallon (17.9 liters) and 50-gallon drum (189 liters).

STORAGE AND HANDLING

All materials shall have proper identification & labels. All containers must have airtight unbroken seals. All materials must be stored in a secure area to prevent theft, damage, or vandalism. Any containers without proper manufacturer's identification will not be acceptable. All materials at jobsite must have proper safety data sheets available at the project site. All materials are to be stored at no less than 45°F. Shelf life is 12 months from date of manufacture with proper storage and handling. Do not store in temperatures above 90°F.

ALL ACRYLIC COATINGS MUST BE PROTECTED FROM FREEZING AT ALL TIMES.

APPLICATION EQUIPMENT

Apply by brush, roller, or airless spray.

1. Brush: Suitable for small areas and flashings. Use a synthetic bristle paint brush.
2. Roller: Recommended when coating small areas. Use a long (1.25") napped roller.
3. Airless Spray Equipment: The following minimums are recommended by MuleHide:
 - a) Pump: 1.6 gal/min output; 2,500 psi
 - b) Gun/Tip: Airless handgun. Reversible tip with orifice sizes ranging from 0.19–0.25 and a fan angle of 40° or 50°.
 - c) Hose: Minimum inside diameter of high-pressure nylon hose of 3/8" to 100'; for any hose over 200' the inside diameter should be 1/2".
 - d) Refer to equipment manufacturer product guidelines.
4. Application rate is 0.5 to 1-gallons per 100 square feet (8-16 wet mils) maximum. Rust areas must be encapsulated.

TYPICAL PROPERTIES AND CHARACTERISTICS

Property	Method	Value
Viscosity (DUF)	90 (+/-3)%	5,000-20,000
Weight/gal (lb)	ASTM D1475	10 ± 0.5
Solids Weight (%)	ASTM D1644	48 ± 3
Solids Volume (%)	ASTM D2697	42 ± 3
VOC (gm/L)	Calculated	< 50
pH (rating)	Std Method	> 9.2
Flash Point (F)	PMCC	> 212

*Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

PRE-APPLICATION

ALWAYS TEST FOR PROPER ADHESION. MuleHide recommends jobsite adhesion tests be performed when the substrate is a factory painted or previously field coated metal panel. Acrylic and silicone systems cannot be installed over Kynar painted panels or metal roof panels that have been coated with aluminum coatings. Aluminum roof coatings must be removed prior to application of acrylic or silicone products. A-125 will not adhere well to a Kynar finished metal surface. If in doubt as to the compatibility of the coating or painted metal surface, MuleHide recommends adhesion tests allowing a minimum six day cure from preparing to performing adhesion tests. All surfaces to be tested must be clean, dry, and free of oil, grease, dirt or loose rust. Various sound and tightly adhered existing coatings require adhesion tests with the coating intended for application to the roof surface. If the new coating fails the adhesion tests, contact MuleHide Technical Department for alternative products.

Before application of the A-125, any loosely adhered materials must be removed and surfaces must be power-washed clean with MuleHide 115 Cleaner. The surface may be damp but must be free of standing water. Mechanically mix before using. Do not store above 90°F. Apply only at temperatures above 40°F and rising with less than 90% humidity and no threat of rain for 48 hours.

APPLICATION

- Stir well prior to application.
- A-125 should be applied at a maximum rate of 0.5 to 1-gallons per 100 square feet (approximately 8-16 wet mils or 2.8 – 5.2 dry mils thick).
- Apply only when temperatures are between 50°F and 120°F. Cool temperatures and high humidity are factors that may retard curing, which can result in longer cure times between coats.
- Do not thin product. Do not heat outside of container.
- Do not apply if there is a threat of inclement weather within 24 hours of



A-125 Metal Roof Primer

Rust Inhibitive Primer



PRODUCT DATA SHEET

application.

- MuleHide recommends a minimum of 12 hours cure time of the A-125 prior to application of acrylic or silicone coatings. The product should be sufficiently dry that foot traffic will not damage the coating. A-125 should be coated within 72 hours to minimize or prevent contamination that would require additional cleaning.
- Applying the product too thick or at high surface temperatures (over 100°F) may also result in splitting, blistering and loss of adhesion.
- Commencement of work by the contractor implies his approval of the deck surface.

CLEAN UP

For clean-up, use 115 Cleaner (or soap) and water while the product is still wet. Thoroughly rinse all hoses and spray equipment at the end of each day and make sure all materials, debris, and containers are removed from the job site and properly store or discard. DO NOT USE MINERAL SPIRITS, XYLENE, TOLUENE, OR VMP & NAPHTHA SOLVENTS.

PRECAUTIONS

- When applied to areas that retain water more than 48 hours service life will be severely diminished and adhesion failure can be expected.
- Avoid prolonged contact with or inhalation of fumes.
- Do not take internally. If swallowed, do not induce vomiting. Contact medical personnel immediately.
- Read safety data sheet prior to use.
- For Professional Use Only - Keep out of the reach of children.
- Do not apply at application rates thicker than recommended.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Phoenix, AZ
- Waco, TX
- Winter Haven, FL

PROTECTION & SAFETY

MuleHide maintains safety data sheets on all of its non-exempt products. Safety data sheets contain health and safety information for your development of appropriate product handling procedures to protect your employees and customers. MuleHide's safety data sheets should be read and understood by all of your supervisory personnel and employees before using MuleHide products in your facilities.

ADDITIONAL INFORMATION

The information given on this PDS is subject to change without notice. Always check the MuleHide website at www.mulehide.com for the latest information, changes and updates or contact MuleHide at 800-786-1492.

DISCLAIMER

The statements provided concerning the material shown are intended as a guide for material usage and are believed to be true and accurate at the time of printing. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. ("MuleHide"). Since the manner of use is beyond our control, MuleHide does not authorize anyone to make any warranty of merchantability or fitness for any particular purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material. This product may be eligible for a MuleHide warranty, please check the MuleHide website at www.mulehide.com or contact MuleHide directly at 800-786-1492 for details. Buyer and user accept the product under these conditions and assume the risk of any failure, any injury to person or property (including that of the user), loss or liability resulting from the handling, storage or use of the product whether or not it is handled, stored or used in accordance with the directions or specifications. MuleHide must be notified in writing of any claims and be given the opportunity to inspect the alleged failure before repairs are made.