



VapAir Seal MD

Air and Vapor Barrier

PRODUCT DATA SHEET

DESCRIPTION

VapAir Seal MD Air and Vapor Barrier is used for direct application over metal decks when insulation is to be mechanically fastened and is suitable for all internal conditions, including very high humidity. VapAir Seal MD air and vapor barrier is quick to install and creates an air- and vapor-tight seal. Its enhanced vapor resistance is sufficient to accommodate extreme internal conditions such as buildings containing wet industrial processes, breweries, swimming pools, sports halls, kitchens, and bathrooms, etc.

VapAir Seal MD consists of a reinforced composite aluminum foil with a tenacious self-adhesive SBS backing and removable poly release film.

FEATURES AND BENEFITS

- Self-adhering.
- Cold-applied.
- Create an airtight and vapor-tight seal.
- Extremely high tear resistance.
- Withstand foot traffic on profiled metal decking, without puncturing.
- Can be bonded with at ambient temperatures of 30°F (-1°C)-40°F (4°C) if material is kept above 50°F (10°C).
- Reduced fire load – has a calorific value of $\leq 10,500$ kJ/m² and complies fully with fire protection requirements for reduced fire load vapor barriers – meets FM requirements.
- Fully complies with FM Approval Standard Class No. 4470.

COVERAGE RATE

Standard roll size of 42.5" wide x 131.23' long will cover approximately 460 ft².

*Effective coverage rate is 420 ft² after seaming.

PRECAUTIONS

- Materials must be kept above 60°F prior to install.
- Rolls must be protected from long exposure to UV rays.
- It is not intended as a temporary roof.
- Only use when insulation is mechanically fastened.
- Must be used on metal decking only.
- Sunglasses that filter ultraviolet light are strongly recommended as aluminum surfaces are highly reflective to sunlight. Roofing technicians should dress appropriately and wear sunscreen protection.
- Primer is not required when applying MD to the metal deck substrate.
- It is recommended to use AeroWeb, 702 or 702LV when temperatures are below 40°F. All other substrates must be primed.

PACKAGING

Size/Weight: 42.5" x 121' / 28 lbs.

Actual Coverage Rate: 458 ft²

STORAGE & HANDLING

- In their original packed condition, the rolls have a shelf life of 12 months. They should be stored upright in a cool, dry environment.
- VapAir Seal MD vapor barriers must be transported and stored on end, in their original packaging. Pallets are wrapped in a gray, light reflecting, UV-protective plastic film. Rolls should remain under this cover until ready for use.
- When working in strong sunlight, it is important to ensure that rolls taken from the pallet are installed immediately. Rolls left on the pallet should remain under the above-mentioned protective cover until ready to be installed.

APPLICATION

1. Surface must be dry and clean from debris.
2. Primer is required on all substrates except for metal substrate.
3. Roll the VapAir Seal MD out flat, without creases.
4. Align and set the position.
5. Overlaps must be at least 2".
6. Remove the release film.
7. Press the sheet down uniformly using, for example, a wide broom. All laps must be rolled down using a hand roller.
8. On profiled decking, end laps in the VapAir Seal MD should be laid over with an additional strip of VapAir Seal MD or flat metal plate, approximately 6" wide, for support.
9. Any large gaps at angle change must be filled in with insulation to support membrane.
10. Install roofing system on the same day.

RATINGS AND CERTIFICATIONS

Physical Property	Standard	Results
FM Approval	FM Standard Class No. 4470	Class 1

LEED INFORMATION

Pre-consumer Recycled Content	0%
Post-consumer Recycled Content	0%
Manufacturing Location	Germany
Solar Reflectance Index (SRI)	N/A



VapAir Seal MD

Air and Vapor Barrier

PRODUCT DATA SHEET

TYPICAL PROPERTIES AND CHARACTERISTICS

Physical Property	Standard	Typical
Overall Thickness	ASTM D5147	.015"
Weight	EN 1849-2	0.06 lb/sf
Rolls per Pallet		24 rolls
Roll Length		131.23'
Roll Width		42.5"
Tensile Strength	ASTM D412	250 psi
Elongation	ASTM D1970ff	330%
Low Temperature Flexibility	ASTM D1970	-20°C
Air Permeance	ASTM E2178	0.000 L*m ² @75 Pa
Hydrostatic Pressure Test (water column 2m high for 15 mins)	AATCC 127	Pass
Peel Adhesion	ASTM D903	14 lb
Water Vapor Permeability sd-value	ASTM E95 D1970	.03 perms
Water Vapor Resistance	BS EN ISO 12572	4,310 MNs/g
Tear Strength	ASTM D1970	135 lbf
Puncture Resistance	ASTM D5602	54.6 lb
Calorific Value	DIN 51900-1	≤10,500 kJ/m ²

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product.
This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

PROTECTION & SAFETY

MuleHide maintains safety data sheets on all of its non-exempt products. Safety data sheets contain health and safety information for your development of appropriate product handling procedures to protect your employees and customers. MuleHide's safety data sheets should be read and understood by all of your supervisory personnel and employees before using MuleHide products in your facilities.

ADDITIONAL INFORMATION

The information given on this PDS is subject to change without notice. Always check the MuleHide website at www.mulehide.com for the latest information, changes and updates or contact MuleHide at 800-786-1492.

DISCLAIMER

The statements provided concerning the material shown are intended as a guide for material usage and are believed to be true and accurate at the time of printing. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. ("MuleHide"). Since the manner of use is beyond our control, MuleHide does not authorize anyone to make any warranty of merchantability or fitness for any particular purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material. This product may be eligible for a MuleHide warranty, please check the MuleHide website at www.mulehide.com or contact MuleHide directly at 800-786-1492 for details. Buyer and user accept the product under these conditions and assume the risk of any failure, any injury to person or property (including that of the user), loss or liability resulting from the handling, storage or use of the product whether or not it is handled, stored or used in accordance with the directions or specifications. MuleHide must be notified in writing of any claims and be given the opportunity to inspect the alleged failure before repairs are made.