



White-on-Black Reinforced EPDM Membrane

60-mil Reinforced Membrane

PRODUCT DATA SHEET



DESCRIPTION

White-on-Black Reinforced EPDM membrane (60-mil) is a high-performance polyester reinforced membrane that stands up to tearing, impacts, punctures, and normal roof traffic. The elastomeric properties of the EPDM sheet compensates for thermal shock and building movement. EPDM membranes provide excellent resistance to ozone and aging. These membranes are manufactured in accordance with the guidelines established by the RMA (Rubber Manufacturers Association) and meet or exceed ASTM Standard Specification D 4637, Type II.

BASIC USES

Our White-on-Black Reinforced EPDM membrane is used in mechanically attached and fully adhered roofing systems in new construction, reroofing and recover (retrofit) applications. It may also be used as flexible membrane flashings for walls, curbs, etc. when installing an EPDM membrane roofing systems. The system must be installed over acceptable roof insulation or other suitable substrate. See the MuleHide EPDM Specifications Manual for complete specifications and details.

LEED INFORMATION

Pre-consumer Recycled Content	0%
Post-consumer Recycled Content	0%
Manufacturing Location	Carlisle, PA
Solar Reflectance Index (SRI)	95
Corporate Sustainability Report	Yes

BENEFITS AND SUPPLEMENTAL STATEMENTS

- Can be installed over a variety of roof decks.
- Outstanding weatherability.
- Sheets can be pre-taped for labor savings and consistent seam placement.
- Requires no special equipment to install.
- Available as a lightweight system.
- Full line of pre-taped accessories available.

TYPICAL PROPERTIES AND CHARACTERISTICS

Physical Property	Test Method	SPEC. (PASS)	Typical
Tolerance on Nominal Thickness, %	ASTM D751	±10	±10
Thickness Over Scrim, min, in. (mm)	ASTM D4637 Annex	0.015 (0.381)	0.025 (0.635)
Weight, lbm/ft ² (kg/m ²) .060			0.40 (2.0)
Breaking Strength, min, lbf (N) .060	ASTM D751 Grab Method CD	90 (400)	225 (996)
Elongation, Ultimate, min, % .060	ASTM D412 Die C	250**	480**
Tearing Strength, min, lbf (N) .060	ASTM D751 B Tongue Tear	10 (45)	70 (311)
Brittleness Point, max, °F (°C)*	ASTM D2137	-49 (-45)	-49 (-45)
Resistance to Heat Aging* Properties after 28 days @ 240°F (116°C) Breaking Strength, min, lbf (N) Elongation, Ultimate, min, % Linear Dimensional Change, max, %	ASTM D573 ASTM D751 ASTM D412 ASTM D1204	 80 (355) 200** ±1.0	 1450 (10.0) 250** -1.0
Ozone Resistance* Condition after exposure to 100 pphm Ozone in air for 168 hrs @ 104°F (40°C) Specimen wrapped around 3" mandrel	ASTM D1149	No Cracks	No Cracks
Resistance to Water Absorption* After 7 days immersion @ 158°F (70°C) Change in mass, max, %	ASTM D471	+8, -2**	5.2**
Water Vapor Permeance* Max, perms	ASTM E 96 (Proc. B or BW)	0.10	0.02
Fungi Resistance	ASTM G21	N/A	0 (no growth)
Specular Gloss at 85°C	ASTM D523	N/A	3
Resistance to Outdoor (Ultraviolet) Weathering* Xenon-Arc, total radiant exposure at 0.70 W/m ² irradiance, 80°C black panel temperature	AST G155	No Cracks No Cracking 2,520 kJ/m ² 1,000 hrs	No Cracks No Cracking 25,200 kJ/m ² 10,000 hrs
At 0.35 W/m ² irradiance, 80°C black panel temperature		2,000 hrs	20,000 hrs



White-on-Black Reinforced EPDM Membrane

60-mil Reinforced Membrane

PRODUCT DATA SHEET

CODE APPROVALS/COMPLIANCE

A variety of Factory Mutual Ratings, Underwriters Laboratories Classifications and Miami-Dade Approvals are available. Contact MuleHide Warranty Department for additional information. Meets or exceeds requirements of ASTM D 4637, Type II for reinforced EPDM single-ply roofing membranes.

INSTALLATION INSTRUCTIONS

1. Approved insulation shall be attached to the roof deck with an approved insulation adhesive or approved fasteners and plates. Install insulation with its largest dimension perpendicular to the direction of the membrane seams where possible.
2. Mechanically Attached Roofing System
 - a. Perimeter sheets to be installed in an approved pattern along all exterior roof edges.
 - b. Mechanical fasteners and plates are installed in the seams of both the perimeter sheets and field sheets and into the roof deck. Use approved fasteners and maintain proper penetration for specific roof deck.
3. Fully Adhered Roofing System
 - a. Perimeter sheets are not required.
 - b. The membrane is required to be mechanically attached at the base of all vertical surfaces, roof edges, and angle changes.
 - c. The field of the roof is fully adhered to the substrate with MuleHide membrane adhesive.
4. All seams are made with MuleHide Tape Primer and White In-Seam Tape.
5. All details will be done in accordance with MuleHide details.
6. This is only a brief summary and not the complete specification. MuleHide Specifications, Details, Technical Bulletins, and associated documents should be thoroughly reviewed prior to starting any project. Contact MuleHide for additional information.

STORAGE AND HANDLING

- Use proper stacking procedures to ensure sufficient stability of the materials.
- Surfaces may be slippery when wet, or due to frost and ice build-up. Exercise caution to prevent falls.
- Exercise care when working near edge of roof.
- Store MuleHide membrane in original wrappings in a cool, shaded area. Cover with light colored, breathable, waterproof tarpaulins.
- Pre-Taped membranes should not be exposed to prolonged jobsite storage temperatures in excess of 90°F (32°C), otherwise the shelf life of the Pre-Tape may be affected.
- When using pre-taped membranes in warm, sunny weather, shade the tape end of the rolls until ready to use.
- MuleHide Pre-Tape has a shelf life of one year.

PROTECTION & SAFETY

MuleHide maintains safety data sheets on all of its non-exempt products. Safety data sheets contain health and safety information for your development of appropriate product handling procedures to protect your employees and customers. MuleHide's safety data sheets should be read and understood by all of your supervisory personnel and employees before using MuleHide products in your facilities.

SUPPLEMENTAL APPROVALS, STATEMENTS AND CHARACTERISTICS

RADIATIVE PROPERTIES FOR CRRC AND LEED		
DESCRIPTION	TEST METHOD	WHITE EPDM
CRRC initial solar reflectance	ASTM C1549	0.77
CRRC solar reflectance after 3 yrs.	ASTM C1549 (uncleaned)	0.66
CRRC initial thermal emittance	ASTM C1371	0.84
CRRC thermal emittance after 3 yrs.	ASTM C1371 (uncleaned)	0.87
SRI (Solar Reflectance Index)	ASTM E1980/ aged 3 yrs.	95/80

ADDITIONAL INFORMATION

On projects where a MuleHide standard or premium warranty is requested, an authorized MuleHide representative shall inspect all completed work.

The information given on this PDS is subject to change without notice. Always check the MuleHide website at www.mulehide.com for the latest information, changes and updates or contact MuleHide at 800-786-1492.

DISCLAIMER

The statements provided concerning the material shown are intended as a guide for material usage and are believed to be true and accurate at the time of printing. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. ("MuleHide"). Since the manner of use is beyond our control, MuleHide does not authorize anyone to make any warranty of merchantability or fitness for any particular purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material. This product may be eligible for a MuleHide warranty, please check the MuleHide website at www.mulehide.com or contact MuleHide directly at 800-786-1492 for details. Buyer and user accept the product under these conditions and assume the risk of any failure, any injury to person or property (including that of the user), loss or liability resulting from the handling, storage or use of the product whether or not it is handled, stored or used in accordance with the directions or specifications. MuleHide must be notified in writing of any claims and be given the opportunity to inspect the alleged failure before repairs are made.