



Product Data Sheet A-320 FINISH

PRODUCT DESCRIPTION

Rev May 2022

A-320 FINISH ("A-320") by Mule-Hide is a white, non-yellowing acrylic based elastomeric coating. It exhibits exceptional exterior durability and UV stability, superior flexibility in low temperature environments, and high reflectivity. A-320 FINISH will maintain its white appearance when applied over any mod bit or fresh asphaltic substrates (New smooth BUR or Granulated Cap Sheets less than 5 years old) and areas that periodically pond water (not to exceed 48 hours). A-320 FINISH is formulated to improve resistance to damage caused by periodic ponding. However, A-320 FINISH is not intended as a "cure all" for ponded water situations and prolonged exposure to moisture in ponded areas may be detrimental to A-320 FINISH. Areas where ponded water remains for more than 48 hours may require the installation of new drains to provide proper drainage or tapered insulation and new, compatible roofing materials to create positive drainage to the existing drain system. NRCA guidelines for ponding water state, "If the ponding condition cannot be eliminated, perform more frequent inspections to monitor and maintain the membrane surface affected by the ponding condition. Implement permanent solutions at the time of reroofing."



A-320 FINISH is available in 1 and 5 gallon pails, 55 gallon drums, and 275 gallon totes.

BASIC USES

A-320 FINISH is designed to impart a white, weatherproof seal over a variety of surfaces, such as:

- Asphaltic roof surfaces
 - New Smooth BUR (less than 5 years old)
 - Modified Bitumen
 - Granulated Cap Sheets
- Acrylic Coatings - Used as a topcoat
- Metal Substrates - Used as a topcoat

Use A-320 FINISH in areas where the existing fresh asphalt or aged asphalt based roof system would discolor and stain a conventional white acrylic coating.

TYPICAL PHYSICAL PROPERTIES

Typical Physical Properties	
Weight per Gall	11.7 +/- 0.4 lbs.
Solids - % by Weight	63.2 +/- 3
Solids - % by Volume	51.0 +/- 3
Viscosity – cps	16,000 +/- 1,500
Viscosity – KU	125 +/- 6
pH	>9.0
Service Temperature Range	-45°F to 200°F
V.O.C. Content	36.6 grams per liter

Typical properties and characteristics are based on samples tested and are not guaranteed for all samples of this product. This data and information is intended as a guide and does not reflect the specification range for any particular property of this product.

COLOR

Standard color is WHITE



Product Data Sheet A-320 FINISH

PACKAGING

5-gallon pails, 55-gallon drum, and 275-gallon reusable totes.

STORAGE & HANDLING

All materials shall have proper identification & labels. All containers must have airtight unbroken seals or unopened containers. All materials must be stored in a secure area to prevent theft, damage, or vandalism. Any containers without proper manufacturer's identification will not be acceptable. All materials at jobsite must have proper SDS Sheets available at the project site. All materials are to be stored at not less than 45°F.

ALL ACRYLIC COATINGS MUST BE PROTECTED FROM FREEZING AT ALL TIMES.

BENEFITS & SUPPLEMENTAL STATEMENTS

Resistant to staining from asphaltic products.

TYPICAL PHYSICAL PROPERTIES

Property	Test Method / Condition	Result
Approximate drying time to recoat	75° F @ 50% RH	12 hours
Tensile Strength	ASTM D412	220 psi +/- 25 psi
Elongation	ASTM D412	285% +/- 50%
Hardness, Shore A	ASTM D2240	60 +/- 5
Low Temp. Flexibility	ASTM D412 - 0.5" mandrel	Pass
Weathering Resistance	5000 hrs. Atlas Weatherometer	No Effect

RADIATIVE PROPERTIES

For Cool Roof Rating Council (CRRC)

DESCRIPTION	TEST METHOD	VALUE
CRRC initial solar reflectance	ASTM C1549	0.83
CRRC solar reflectance after 3 years	ASTM C1549	0.66
CRRC initial thermal emittance	ASTM C1371	0.91
CRRC thermal emittance after 3 years	ASTM C1371	0.90

The Cool Roof Rating Council (CRRC) does not specify minimums for reflectance or emittance but they do require specific protocols for testing and reporting. Cleaning of the aged roof surface is **not** permitted for determination of radiative properties after 3 years.

COVERAGE RATES

Coverage rates vary by substrate

INSTALLATION TEMPERATURE

Temperature of surfaces to be coated should be above 45°F and below 110°F. Do not apply material if there is a chance that ambient temperatures may drop below 45°F within 48 hours after application.



Product Data Sheet A-320 FINISH

APPLICATION EQUIPMENT

Application may be by brush, roller, or airless spray.

1. Brush: Suitable for small areas and flashings. Use a synthetic bristle paint brush.
2. Roller: Recommended when coating small areas. Use a medium (1/2") or a long (1.0") napped roller.
3. Airless Spray Equipment: The following spray equipment is recommended by Mule-Hide.

PUMP The pump should be capable of producing a minimum material output of 2 gallons per minute at 3,000 p.s.i.

GUN The airless spray gun should be equipped with a ball bearing swivel for ease of handling. Recommended orifice size is .025 to .035 inch diameter with a wide angle fan pattern. A Reverse-A-Clean nozzle is recommended. Exact orifice size will vary with temperature of the material and weather conditions.

HOSES Maximum of 300' of high-pressure material hose. Hose ID are available from 1/2" to 1/4" Whip hose length should be one (1) ID size smaller than rest of hose length

APPLICATION

SURFACE PREPARATION

ALWAYS TEST FOR PROPER ADHESION. Mule-Hide recommends a jobsite adhesion test be performed. If in doubt as to the compatibility of the coating and substrate, allow a minimum six-day cure. Prior to the application of any Mule-Hide Roof Coatings System, always read all pertinent use, storage, application and safety data.

APPLICATION

Properly clean roof surface scheduled to receive coating, and rinse well. Make all necessary repairs to the existing roof surface in accordance with NRCA recommended procedures. Mule-Hide recommends a minimum finish application rate of 2 gals per 100 square feet. For extended performance A-320 may be applied in two coats at a rate of 1.5 gal per 100 square feet, per coat for a final coverage rate of 3 gals per 100 square feet. Do not apply the A-320 at a coverage rate higher than 2 gal per 100 square feet per coat. Applying the A-320 at coverage rates higher than 2 gal per 100 square feet can result in surface splitting or blistering due to trapped moisture. When applying multiple coats, A-320 should always be applied at a rate of 1.5 gals per 100 square feet or less.

Mule-Hide recommends a 12-hour (approximately) cure time between coats or that the product be sufficiently dry so that foot traffic will not damage the coating. Multiple coats should always be applied within 72 hours of each coat to minimize or prevent contamination that would require additional cleaning. Commencement of work by the contractor implies his approval of the deck surface.

PRECAUTIONS

Check weather conditions prior to start of work. Acrylic Coatings require the complete evaporation of water to cure. Cool temperatures and high humidity retard cure. Do not apply if weather conditions will not permit complete cure before rain, dew or freezing temperatures.

Cool temperatures and high humidity are factors that may delay curing, which can result in longer cure times between coats. For applications in higher temperatures (above 90° F) Mule-Hide recommends application in multiple thin coats to prevent trapped moisture problems.



Product Data Sheet A-320 FINISH

CLEAN UP

Equipment clean up is simple using 115 CLEANER and water while the product is still wet. Thoroughly rinse all hoses and spray equipment at the end of each day and make sure all materials, debris, and containers are removed from the job site and properly store or discard.

PROTECTION & SAFETY

Mule-Hide maintains Material Safety Data Sheets on all of its products. Safety Data Sheets contain health and safety information for your development of appropriate product handling procedures to protect your employees and customers. Mule-Hide's Material Safety Data Sheets should be read and understood by all of your supervisory personnel and employees before using Mule-Hide products in your facilities.

ADDITIONAL INFORMATION

The information given on this PDS is subject to change without notice. Always check the Mule-Hide website at www.mulehide.com for the latest information, changes and updates or contact Mule-Hide Products Company at 800-786-1492.

DISCLAIMER

The statements provided concerning the material shown are intended as a guide for material usage and are believed to be true and accurate at the time of printing. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. Since the manner of use is beyond our control, Mule-Hide does not authorize anyone to make any warranty of merchantability or fitness for any particular purpose or any other warranty, guarantee or representation, expressed or implied, concerning this material. This product may be eligible for a Mule-Hide warranty, please check the Mule-Hide website at www.mulehide.com or contact Mule-Hide directly at 800-786-1492 for details. Buyer and user accept the product under these conditions and assume the risk of any failure, any injury person or property (including that of the user), loss or liability resulting from the handling, storage or use of the product whether or not it is handled, stored or used in accordance with the directions or specifications. Mule-Hide must be notified in writing of any claims and be given the opportunity to inspect the alleged failure before repairs are made.