

F/G Base Sheet

Inorganic Fiberglass Mat Base Sheet



The Professionals Choice for Roofing Products

800-786-1492 • mulehide.com

Rugged • Time Tested • Weather Tested

F/G Base Sheet

Inorganic Fiberglass Mat Base Sheet

Product Description

Tough and durable, F/G Base Sheet can be used as part of built-up roofing (BUR) systems or as the felt layer in steep-slope shingled roofing systems.

The base sheet is made of an inorganic fiberglass mat that has been coated on both sides with a weathering-grade oxidized asphalt blend and surfaced with granular fines. It delivers enhanced weathering and aging characteristics, along with great tear and pull-through resistance.

- In BUR systems, F/G Base Sheet is attached to the flat roof deck or insulation layer using mechanical fasteners or hot asphalt.
- F/G Base Sheet also is suitable for use as a vapor retarder, with a solid mopping of asphaltic material, under roof insulation or between multiple layers of insulation.

Features & Benefits

- Granular fines prevent sticking in the roll.
- Superior pliability and dimensional stability.
- Excellent resistance to punctures and tears.
- Wrinkle-resistant, ensuring it lays flat for easier installation.
- Consistent thickness of the oxidized asphalt blend coating on both sides provides enhanced weatherability.
- Meets or exceeds ASTM D4601-04 Type II (Standard Specification for Asphalt-Coated Glass Fiber Base Sheet Used in Roofing).

Code Approvals/Compliance

Various code approvals are available, including:

- Meets the requirements of ASTM D4601 Type II
- Miami-Dade County approved



Packaging:

- 3 sq. Roll

Code Approvals/Compliance:



D4601-04 Type II

F/G Base Sheet	Roll Size	Coverage	Weight	Carton	Roll/Pallet	Pallet Size
09MH75BASE	100' x 39.375"	324 sq. ft.	72 lbs.	3 Sq. Roll	20	42" x 48"

F/G Base Sheet

Inorganic Fiberglass Mat Base Sheet

Reference Chart - F/G Base Sheet

Physical Property	Data (ASTM D4601-04)
Mass of Base Sheet	37.0 lbs./100 sq. ft.
Mass of Asphalt Coating (min.)	5.6 lbs./100 sq. ft.
Mass of Desaturated Glass Mat	1.55 lbs./100 sq. ft.
Mass of Stabilizer and Surfacing (min.)	70%
Machine Direction Tensile Strength	22 lbf./in.
Cross Direction Tensile Strength	22 lbf./in.
Pliability, (1/2") Radius Maximum Failures	0

Frequently Asked Questions

1. What types of roof decks can F/G Base Sheet be attached to?

F/G Base Sheet can be attached to steel, concrete, and wood roof decks.

2. How is F/G Base Sheet attached?

In BUR systems, F/B Base Sheet is attached to the roof deck or insulation layer using mechanical fasteners or hot asphalt. When used as a vapor retarder, it is installed with a solid mopping of asphaltic material.

3. What warranty coverage is offered for F/G Base Sheet?

F/G Base Sheet is backed by Mule-Hide Product Co.'s standard one-year materials-only warranty.

MORE INFO



The information herein should not be considered all-inclusive and should always be accompanied by a review of the Mule-Hide specifications and guidelines and good application practices.

This information herein is based upon data and knowledge considered to be true and accurate at the time of printing and is provided for the reader's consideration, investigation and verification. No statement made by anyone may supersede this information, except when done in writing by Mule-Hide Products Co., Inc. Mule-Hide Products Co., Inc. does not warrant any results to be obtained. Statements concerning possible use of Mule-Hide products are made without knowledge of your particular roof and such an application may not be fit for your particular purpose. MULE-HIDE DISCLAIMS ALL WARRANTIES, INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, except written warranties attached to Mule-Hide products and written warranties signed by an officer of Mule-Hide.

Visit the Mule-Hide website at www.mulehide.com prior to any installation for updated technical specifications and details. Mule-Hide is a U.S. registered trademark. All rights reserved. REV 0 9/21