



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

SECTION 07 52 00

MODIFIED BITUMINOUS ROOFING SYSTEMS

PART 1 GENERAL

1.1 SECTION INCLUDES

- A. Modified bituminous membrane Self adhered roofing.
- B. Modified bituminous membrane mechanically attached.
- C. Roof Insulation.

1.2 RELATED SECTIONS

- A. Section 03510 – Cast Concrete Decking: Decking and decking substrate preparation
- B. Section 05300 - Metal Decking: Decking and decking substrate preparation.
- C. Section 06100 - Rough Carpentry.
- D. Section 06114 - Wood Blocking and Curbing: Wood nailers and cant strips.
- E. Section 07220 - Insulation Board: Insulation and fastening.
- F. Section 07620 - Sheet Metal Flashing and Trim: Weather protection for base flashings.
- G. Section 07710 - Manufactured Roof Specialties: Counter flashing gravel stops, and fascias.
- H. Section 07724 - Roof Hatches: Frame and integral curb; Counter flashing.
- I. Section 08620 - Unit Skylights: Skylight frame and integral curb and counter flashing.
- J. Section 08630 - Metal-Framed Skylights: Skylight frame and integral curb and counter flashing.
- K. Section 08950 - Translucent Wall and Roof Assemblies: Counter flashing
- L. Section 08960 - Sloped Glazing Assemblies: Counter flashing.
- M. Section 15120 - Piping Specialties: Roof Drains, Sumps.

1.3 REFERENCES

- A. ASTM C1289 - Standard Specification for Faced Rigid Cellular Polyisocyanurate Thermal Insulation Board.
- B. ASTM D41 - Standard Specification for Asphalt Primer Used in Roofing, Damp proofing, and Waterproofing.
- C. ASTM D312 - Standard Specification for Asphalt used in Roofing.
- D. ASTM D1970 - Specification for Sheet Materials, Self-Adhering Polymer Modified Bituminous, Used as Steep Roofing Underlayment for Ice Dam Protection.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

- E. ASTM D6162 - Specification for Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using a Combination of Polyester and Glass Fiber Reinforcements.
- F. ASTM D6163 - Standard Specification for Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using Glass Fiber Reinforcements.
- G. ASTM D6164 - Standard Specification for Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using Polyester Reinforcements.
- H. ASTM D6222 - Standard Specification for Atactic Polypropylene (APP) Modified Bituminous Sheet Materials Using Polyester Reinforcements.
- I. ASTM D6223 - Standard Specification for Atactic Polypropylene (APP) Modified Bituminous Sheet Materials Using a Combination of Polyester and Glass Fiber Reinforcements.
- J. ASTM D6757 - Standard Specification for Underlayment Felt Containing Inorganic Fibers Used in Steep-Slope Roofing.
- K. ASTM D7897 - Standard Practice for Laboratory Soiling and Weathering of Natural Exposure on Solar Reflectance and Thermal Emittance.
- L. NRCA - The NRCA Roofing and Waterproofing Manual. National Roofing Contractors Association (NRCA) - Roofing and Waterproofing Manual.
- M. Sheet Metal and Air Conditioning Contractors National Association, Inc. (SMACNA) - Architectural Sheet Metal Manual.
- N. ANSI-SPRI ES-1 Wind Design Standard for Edge Systems used with Low Slope Roofing Systems.
- O. UL - Fire Resistance Directory.
- P. FM Approvals - Roof Coverings.
- Q. FBC - Florida Building Code.
- R. Miami-Dade Building Code Compliance - N.O.A. (Notice of Acceptance)

1.4 CODE AND TEST REQUIREMENTS

- A. Perform work in accordance with all federal, state and local codes.
- B. Exterior Fire Test Exposure: Roofing system achieving a UL Class rating for roof slopes indicated on the Contract Drawings.
 - 1. [UL Class Rating]
- C. Windstorm Classification: Roofing system, which will achieve the required uplift resistance as calculated in accordance with the most current revision of ASCE 7-16 or determined by the Design Professional, local Code Agency, or Authority having Jurisdiction (AHJ).
- D. Cool Roof Rating Council (CRRC) Reflectivity/Thermal Emittance: Minimum requirements when tested according to CRRC-1
 - 1. Initial Solar Reflectance Index (SRI): Not less than 96.
 - 2. Thermal Emittance: Not less than 0.90.
- E. LEED: Roof system to meet reflectivity and emissivity criteria to qualify for one point under the LEED credit category, Credit 7.2, Sustainable Sites – Heat Island Reduction (Roofs).



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

- F. Roof system to be tested in compliance with the following codes and test requirements:
1. FM Approvals: FM Listed and Approved.
 2. Underwriters Laboratories: Certification TGFU.R13850.
 3. Florida FBC: For use outside Miami-Dade and Broward Counties.
 - a. Membrane Systems FL10497.
 - b. Roofing Cements and Coatings FL41936, FL44613, FL46931.
 4. Miami-Dade County:
 - a. Self-Adhered Membrane Systems Over:
 - 1) [Approved Substrate]
 - b. Roofing Cements and Coatings: MuleHide Coatings and Mastics N.O.A.
 5. International Code Council Evaluation Service (ICC-ES):
 - a. Membrane Systems: ESR-2018.

1.5 SUBMITTALS

- A. Submit under provisions of Section 01300.
- B. Product Data: Manufacturer's data sheets on each product to be used, including:
1. Preparation instructions and recommendations.
 2. Storage and handling requirements and recommendations.
 3. Installation instructions.
- C. Shop Drawings: Shop drawings including installation details of roofing, flashing, fastening and insulation, including notation of roof slopes and fastening patterns of insulation and base modified bitumen membrane, prior to job start.
- D. Design Pressure Calculations: Design pressure calculations for the roof area in accordance with ASCE 7-16 and local Building Code requirements. Include a roof system attachment analysis report, certifying the system's compliance with applicable wind load requirements before Work begins. Report shall be signed and sealed by a Professional Engineer registered in the State of the Project who has provided roof system attachment analysis for not less than 5 consecutive years.
- E. Verification Samples: As required. For each modified bituminous membrane ply product specified, two samples, minimum size 6 inches (150 mm) square, representing actual product, color, and patterns.
- F. Manufacturer's Field Reports: As required.
- G. Manufacturer's Certificates: Certify products meet or exceed specified requirements.

1.6 QUALITY ASSURANCE

- A. Perform Work in accordance with NRCA Roofing and Waterproofing Manual.
- B. Manufacturer Qualifications: Company specializing in manufacturing products specified with ten years documented experience.
- C. As an ISO 9001:2015 Certified Company, MuleHide provides quality products worldwide.
- D. Dependent upon the type of warranty requested or specified, roof observations may be required. MuleHide reserves the right to conduct roof observations to ensure quality of installation.
- E. MuleHide provides installers assistance with a qualified team of technical field representatives. Please contact Technical Services or your local sales representative for information regarding the Technical Representative assigned to your region.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

1.7 PRE-INSTALLATION MEETINGS

- A. Convene minimum one week prior to commencing Work of this section.
- B. Review installation procedures and coordination required with related Work.
- C. Inspect and make notes of job conditions prior to installation:
 - 1. Record minutes of the conference and provide copies to all parties present.
 - 2. Identify outstanding issues in writing designating the responsible party for follow-up action and the timetable for completion.
 - 3. Installation of roofing system shall not begin until all outstanding issues are resolved to the satisfaction of the Architect.

1.8 DELIVERY, STORAGE, AND HANDLING

- A. Ensure all materials are stored in a manner which prevents them being exposed to moisture.
- B. Materials should be examined when received. Damaged or unlabeled materials should not be used.
- C. Materials must be stored in a dry area with adequate ventilation. Care should be taken to only remove stored materials that can be installed in a reasonable amount of time. All excess materials must be kept in storage.
- D. Rolls shall be stored in an upright position with selvage edge up on pallets.
- E. Prior to beginning installation, remove all roll wrapping tape by cutting carefully and not ripping the material.
- F. MuleHide does allow double stacking of pallets of membranes with the use of slip boards. Please see the Technical Bulletin online at www.MuleHide.com for Rotation and Storage of Roll Products.
- G. MuleHide self-adhered membranes to be stored at room temperature (60°F to 80°F) whenever possible and in an upright position on a flat surface. Avoid storing out of packaging for prolonged periods, especially above 88°F (31°C), in direct sunlight. Do not take the roll out of the packaging until it is ready for application. Refer to technical bulletins found at www.MuleHide.com for more instruction on storage and handling.
- H. MuleHide membranes shall remain stored in wraps until time of application.
- I. MuleHide Cold Applied Cements, Adhesives and Mastics shelf life is typically 18 months, if stored in original unopened containers – between 40°F–100°F (4°C– 38°C).
- J. All containers should be sealed when not in use.

1.9 COORDINATION

- A. Coordinate Work with installing associated metal flashings as work of this section proceeds.

1.10 PROJECT CONDITIONS

- A. This specification shall not be considered applicable without the appropriate additional specifications approved by MuleHide if it should be determined that any of the following conditions exist:
 - 1. The installation of any MuleHide Roof System is in a coastal area or high wind zone.
 - 2. If the MuleHide Roof System should exceed the structural load conditions as determined by an architect or Engineer.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

3. When chemical or hazardous materials are discharged onto the MuleHide Roof System.
- B. The minimum application temperature for MuleHide SAMB materials is 40°F and rising for 48 consecutive hours.
 1. In order to perform properly, MuleHide SAMB materials require a minimum application temperature of 40°F and rising for 48 consecutive hours. This applies to the roofing materials and approved substrate. During installation, the membrane must be promptly rolled with a **minimum 75# roller**. Failure to abide by these requirements may result in poor adhesion or cracking issues.
 2. During periods of colder weather, the MuleHide SAMB materials should always be stored at room temperature (60°F to 80°F) until just prior to use. Materials that are not stored at room temperature (or not used within 4 hours) should be restored to room temperature prior to use.
 - C. The General Contractor or the building owner shall be responsible for providing adequate surfaces and structures to receive the insulation, MuleHide Roof System and related sheet metal necessary for the successful completion of the project.
 - D. Only as much new roofing as can be made watertight shall be installed each day. This includes all flashing work.
 - E. All substrates to receive new insulation, membrane or flashing shall be thoroughly dry. Should surface moisture occur, the contractor shall provide adequate equipment to dry the substrate prior to application of new material.
 - F. Prior to and during application, all dirt, debris and dust shall be removed from surfaces to be roofed for both new and reroofing substrates.
 - G. On all projects where the SBS or APP Self-Adhering Modified Bitumen Roofing System is specified, it is the responsibility of the independent roofing contractor to have the owner or owner's representative verify the condition of the deck or substrate and to confirm the roof deck can withstand the additional load.
 - H. Precautions shall be taken to prevent wind blow-off or wind damage during the course of the roofing application. This may necessitate additional securement of temporary construction, materials and equipment.
 - I. The contractor shall verify and ensure that all roof drain lines are unblocked before starting work. Any blockages found shall be reported to the owner's representative and MuleHide's Technical Service Department in writing.
 - J. Temporary waterstops shall be installed at the end of each day's work. Temporary waterstops shall be removed at the start of the next day's work and disposed of properly. Waterstops shall be compatible with all materials.
 - K. Do not install the MuleHide Self-Adhering Modified Bitumen Roofing Membrane in direct contact with any product containing coal tar pitch, creosote or penta-based materials. Consult the MuleHide Technical Service Department for special installation requirements.
 - L. Do not allow contaminants such as petroleum, grease, acid, solvents, vegetable or mineral oil, animal oil, animal fat, etc. or direct steam venting to come into direct contact with the MuleHide Self-Adhering Modified Bitumen Roofing Membrane. Contact the MuleHide Technical Service Department for recommendations if such conditions exist.
 - M. The contractor shall follow and comply with all safety regulations as recommended by OSHA.
 - N. All work shall be scheduled and executed without exposing interior building areas to the effects of inclement weather. The existing building and its contents shall be protected against all risks.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

- O. Arrange work sequence to avoid use of newly constructed roofing for storage, walking surfaces and equipment movement. Contractor shall provide all necessary protection and barriers to segregate the work areas and prevent damage to adjacent areas. If excessive traffic over newly installed membrane is necessary, contractor shall provide plywood or polyester felt protection to prevent damage. All damaged materials shall be replaced with new materials.
- P. Arrange work sequence to avoid use of newly constructed roofing for storage, walking surfaces and equipment movement. Contractor shall provide all necessary protection and barriers to segregate the work areas and prevent damage to adjacent areas. If excessive traffic over newly installed membrane is necessary, contractor shall provide plywood or polyester felt protection to prevent damage. All damaged materials shall be replaced with new materials.
- Q. Any unusual or concealed condition discovered during the course of the work is to be reported immediately in writing to the owner and MuleHide's Technical Service Department. Work is to be halted until the owner has responded with a solution to the problems.
- R. Vapor Retarders
 - 1. MuleHide does not require a vapor retarder for the protection of the membrane; however, it should be considered by the specifier for the protection of the roofing assembly (i.e. primarily insulation, underlayment and adhesives). The following criteria should be considered by the specifier:
 - a. Use of a vapor retarder to protect insulation and reduce moisture accumulation within an insulated roofing assembly, should be investigated by the specifier. Consult latest publications by ASHRAE (American Society of Heating, Refrigerating and Air-Conditioning Engineers, Inc.), NRCA (National Roofing Contractors Association), local building and energy codes for specific information.
 - b. In the generally temperate climate of the United States, during the winter months, water vapor flows upward from a heated, more humid interior toward a colder, drier exterior. Vapor retarders are more commonly required in northern climates than in southern regions, where downward vapor pressure may be expected and the roofing membrane itself becomes the vapor retarder.
 - c. On cold storage/freezer facilities, the perimeter and penetration details must be selected to provide an air seal and prevent outside air from infiltrating and condensing within the roofing assembly.
 - 2. When a vapor retarder is specified, MuleHide F5 Air & Vapor Barrier may be used. Refer to F5 Air & Vapor Barrier Product Data Sheet for product installation.
- S. On structural concrete decks, when a vapor retarder is not used, gaps in the deck along the perimeter and around penetrations must be sealed. If tilt-up panels are present, vertical joints between panels must be sealed as well. Sealing these areas will help prevent infiltration of hot, humid air and possible moisture contamination resulting from condensation. This is specifically important when adhesive is used to attach the roof insulation.
- T. All local building codes, energy codes and requirements should be followed where applicable. It is the roofing contractor's sole responsibility to determine and ensure that the roofing system selected complies with all local codes and requirements.
- U. Both interior and exterior building areas affected by construction shall be cleaned up and any damaged areas shall be repaired to the owner's satisfaction.
- V. Certain project conditions may require modifications to this specification. Contact the MuleHide Technical Service Department if any of the following conditions exist:
 - a. Roof heights greater than 100 feet.
 - b. Geographical location in a 100 mph or greater wind zone, per the ANSI 100 year mean recurrence interval wind isotach.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

- c. Location with Exposure D as determined in ANSI A58.1.

1.11 WARRANTY

All MuleHide warranties are available for commercial projects. A Roofing Membrane Limited Warranty for a maximum of 20 years is available for residential projects.

A. MuleHide's Roofing Membrane Limited Warranty

MuleHide offers a 10, 12, 15, or 20-year Roofing Membrane Limited Warranty ("Warranty") for a charge. The Warranty covers only the MuleHide membrane (or portion thereof) determined by MuleHide to be defective and resulting in roof leaks. This Warranty does not cover workmanship or other components not supplied by MuleHide. MuleHide does not perform inspections of the installation before issuing the Roofing Membrane Limited Warranty. A MuleHide Warranty Application and any associated warranty fee must be submitted to MuleHide to obtain this warranty. Proof of purchase may be required.

1. Projects utilizing the SA-SBS Cap Sheet or SA-APP Cap Sheet may only obtain a 10 or 12-year Roofing Membrane Limited Warranty.
2. Projects requesting a 15-year Roofing Membrane Limited Warranty require the use of the SA-SBS Cap Sheet or SA-APP Cap Sheet and one layer of SA-Base applied over an approved substrate. Proof of purchase may be required.
3. Projects requesting a 20-year Roofing Membrane Limited Warranty require the use of the SA-SBS Cap Sheet or SA-APP Cap Sheet and two layers of SA-Base applied over an approved substrate. Proof of purchase may be required.

B. MuleHide Modified Bitumen System Warranty

MuleHide offers a 10, 15, or 20-year Self-Adhering Modified Bitumen System Warranty ("System Warranty") for commercial projects for a charge. The System Warranty is a "No Dollar Limit", labor and material warranty that covers the MuleHide labeled membranes, insulation, other components supplied by MuleHide and approved products (such as insulation adhesive or other pre-approved accessories) installed by a MuleHide Warranty Eligible Contractor. A MuleHide Warranty Eligible Contractor must submit a Warranty Application and the appropriate fee to MuleHide. MuleHide recommends that all Warranty Applications be submitted for review prior to bidding the project. System Warranties require inspections by a MuleHide representative.

1. Projects requesting a 10-year Self-Adhering Modified Bitumen System Warranty require the use of the SA-SBS Cap Sheet or SA-APP Cap Sheet applied over an approved MuleHide insulation, coverboard or base sheet.
2. Projects requesting a 15-year Modified Bitumen System Warranty require the use of SA-SBS Cap Sheet or SA-APP Cap Sheet and one layer of SA-Base applied over an approved MuleHide insulation, coverboard or base sheet.
3. Projects requesting a 20-year Modified Bitumen System Warranty require the use SA-SBS Cap Sheet or SA-APP Cap Sheet and two layers of SA-Base applied over an approved MuleHide insulation, coverboard or base sheet.

- C. MuleHide is under no obligation to issue warranties on projects completed prior to submittal to the MuleHide Technical Service Department of a properly completed Warranty Application.

- D. Metal flashing products supplied by MuleHide (MuleHide Metal Accessories) and installed by a MuleHide Warranty Eligible Contractor will be covered under the NDL System Warranty. The finish on



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

the MuleHide labeled metal components are covered for a maximum warranty period for up to 25-years independent of the terms of the issued warranty (see the MuleHide 25-years Limited Metal Warranty for specific warranty coverage).

- E. NDL System warranties are not available for residential projects.
- F. Tie-ins are not covered by MuleHide warranties.
- G. Contact MuleHide Technical Service Department for other extended warranties that may be available.
- H. Terms and Conditions of Warranties.
 - 1. MuleHide's obligations under the Roofing Membrane Limited Warranty and the NDL System Warranty are limited to the specific terms and conditions of the respective Warranties. Sample copies of the MuleHide Warranties are available from the MuleHide Technical Service Department upon request.
 - 2. MuleHide does not warrant products incorporated or utilized in the installation that were not furnished or approved by MuleHide.

PART 2 PRODUCTS

2.1 MANUFACTURERS

- A. Acceptable Manufacturer: MuleHide Products Co., Inc., which is located at: 1195 Prince Hall Drive.; Beloit, WI 53511; Toll Free Tel: 800-786-1492; Web: www.MuleHide.com Email: requestinfo@marketing@MuleHide.com.
- B. Substitutions: Not permitted.
- C. Requests for substitutions will be considered in accordance with provisions of Section 01600.

2.2 INSULATION

- A. Wood Nailers
 - 1. Nailers shall be #2 or better lumber. Creosote and asphaltic preservatives are not acceptable. Pressure treated lumber is not required on new construction unless specified by the architect.
 - 2. Wood nailers shall conform to Factory Mutual's Loss Prevention Data Sheet 1-49.
 - 3. Wood nailers shall be installed as specified on the project drawings and shall be of a height sufficient to match the thickness of the insulation being used.
- B. Insulation
 - 1. Insulation shall be installed as a protection layer over the existing substrate or to obtain a desired thermal value.
 - 2. Insulation shall be compatible with the MuleHide Self-Adhering Modified Bitumen Membranes, MuleHide Adhesives, and other MuleHide Accessories.
 - 3. All surfaces to receive SA membranes are to be clean, dry and free of any contaminants that could adversely affect adhesion of the product, such as gypsum dust or other debris.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

4. The following insulation/cover boards are acceptable for use with a self-adhering modified bitumen roofing system when a NDL System Warranty is requested:
 - a. MuleHide Poly ISO 1 or MuleHide Poly ISO 2 polyisocyanurate insulation meeting the physical property requirements of Fed. Spec HH-I-1972 and having a minimum compressive resistance of 18 psi. Thickness minimum is 1.0" or greater as required to span steel deck flutes.
 - b. High Density (HD) Wood Fiberboards
 - 1 Structodek[®] HD with Primed Red Coating high density wood fiberboard by Blue Ridge - may be used as an overlay over other insulations. 1/2-inch thick is the minimum requirement when used as an overlay. MuleHide requires a minimum 1-inch thick board when installing directly over steel decks. Wood and concrete decks require a minimum 1/2-inch thick board. Minimum thicknesses and attachment rates will vary with wind requirements and deck types.
 - 2 HD Wood Fiberboard – Asphalt impregnated, coated six sides
 - c. Expanded Polystyrene (EPS). Density of boards must be 1.0 PCF certified minimum and meeting ASTM C578, Type II physical properties. Minimum thickness shall be 1.0 inch. When installing directly over a steel deck the minimum thickness shall be as required by insulation manufacturer to span flutes. An overlay of a minimum 1/2" thick HD Wood Fiberboard, minimum 1" polyisocyanurate insulation, minimum 1/4" DensDeck, or minimum 1/4" Securock is required. Check local building codes as a layer of gypsum board may be required under the EPS insulation (on steel decks).
 - d. Extruded Polystyrene meeting ASTM C578, Types IV, VI or VII physical properties. Minimum thickness shall be 1.0 inch. When installing directly over a steel deck the minimum thickness shall be as required by insulation manufacturer to span flutes. An overlay of a minimum 1/2" thick HD Wood Fiberboard, minimum 1" polyisocyanurate insulation, minimum 1/4" DensDeck, or minimum 1/4" Securock is required. Check local building codes as a layer of gypsum board may be required under the extruded insulation (on steel decks).
 - e. DensDeck Prime or Securock - A minimum 1/4" thick layer of DensDeck Prime or Securock Gypsum-Fiber Roof Board may be used as an overlay over an approved insulation or as a thermal barrier over a combustible deck. Priming of DensDeck Prime with #121 Asphalt Primer is not required (unless contaminants such as gypsum dust are present), but if primer is applied it will enhance adhesion.
 - f. State and local building codes should be reviewed regarding the installation of expanded or extruded polystyrene insulation directly over a steel deck.
5. Insulation manufacturer shall provide its recommendations for use and attachment to the owner with a copy sent to MuleHide's Technical Service Department. In addition, the insulation manufacturer shall provide a copy of their specific warranty conditions.
6. MuleHide NDL System Warranties require the use of the MuleHide labeled insulation or insulation provided by a MuleHide approved manufacturer. Use of other insulations may disqualify the project for consideration of the issuance of an NDL System Warranty. Contact the MuleHide Technical Department for specific requirements.
7. Following is a list of **Non-Acceptable** insulations/substrate material.
 - a. Perlite (as a top layer)
 - b. Foil-faced polyisocyanurate insulation
 - c. Direct adhesion to Extruded and Expanded polystyrene
 - d. Cementitious boards
 - e. Wood Fiberboard (standard density)
 - f. DensDeck (standard un-primed board)



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

- g. Lightweight Concrete
- h. Sand surfaced base sheets
- i. 15 lb & 30 lb felts

- 8. If a substrate or insulation is not listed or not acceptable, the installation of MuleHide Nail Base is an option to provide a suitable substrate to build the system on.

C. UL and FM Approved Assemblies

Contact MuleHide Technical Department for proper insulated assemblies when projects require compliance with UL or FM requirements. The components may change with the slope, deck type and classification requested.

D. Sheet Metal

- 1. Metal flashing products supplied by MuleHide (MuleHide Metal Accessories) and installed by a MuleHide Warranty Eligible Contractor can be covered under an NDL System Warranty.
- 2. Metal components such as gravel stops, drip aprons, counterflashings, copings, etc., should be fabricated and installed in accordance ES-1 recommendations and requirements.
 - 3. Sheet metal components supplied by others are not covered by the MuleHide warranties. Contact MuleHide's Technical Service Department for specific requirements.

2.3 MODIFIED BITUMINOUS ROOFING MEMBRANE

- A. Base Sheet: (Optional depending on system)
 - 1. SA Base and Nail Base
 - a. ASTM: D6163 - Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using Fiberglass Reinforcements
 - b. Reinforcement: Fiberglass
 - c. Type: I
 - d. Thickness: 80 mils [2.0 mm] and 80 mils [2.0 mm] (Respectively)
 - 2. Method of application: Self Adhered or Mechanically Attached
- B. Interply Sheet (Optional 2 plies can be installed per project specifications):
 - 1. SA Base
 - e. ASTM: D6163 - Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using Fiberglass Reinforcements
 - f. Reinforcement: Fiberglass
 - g. Type: I
 - h. Thickness: 80 mils [2.0 mm]
 - i. Available in FR
 - 2. Method of application: Self Adhered
- C. Granulated Surfaced Cap Sheet:
 - 1. SA-SBS Cap Sheet or SA-APP Cap Sheet or SA-APP Koolcap
 - a. ASTM: D6164 - Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using Polyester Reinforcements , ASTM D6222
 - b. Reinforcement: Polyester
 - c. Type: I
 - d. Thickness: 140 mils [3.5 mm] , 142 mils [3.6 mm] , 160 mils [4.0 mm]
 - e. Available in FR



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

2. Method of application: Self Adhered

2.4 FLASHINGS

A. WALL FLASHINGS

1. Same as Field: Minimum of 1 ply of base/interply as reinforcement and cap sheet for all flashing systems.

B. PENETRATION FLASHINGS

1. Type of flashings: Liquid Applied
 - a) Liqui-Flash
 - i. Could be installed in 3-course fashion using Reinforcing Polyester Fabric.

2.5 FASTENERS

- A. Fasteners and Plates: Provide FM or MuleHide Approved fasteners and plates and other devices as required to suit the system specified.
- B. Wood: Roofing nails of galvanized or stainless steel, of length to penetrate the wood by at least 3/4 inch (19 mm) on flashings and parapet walls.
- C. Masonry: Nail-in expansion type device with zinc body, plated steel nail, and mushroom head or approved equal and of length to embed into the masonry a minimum of 1 inch (25 mm).
- D. Insulation: Mechanical fasteners for securing of insulation to decking shall be approved by the insulation manufacturer for the system specified and shall be FM Approved and be in compliance with Appendix "E" of FM 4470 for corrosion resistance.
 1. Use the same brand fastener throughout the work.
 2. Provide the number of fasteners and layout as recommended by the manufacturer and per FM Approvals.
 3. Determine length of fastener by the thickness of the decking and any fill and the thickness of the insulation. Fasteners shall be of sufficient length to achieve a minimum of 1 inch (25 mm) penetration.
- E. Pre-Assembled Fastener/Plate Combination: Case hardened carbon steel and use specific head, shank and thread diameters, point types and head styles meeting building code and FM approvals for corrosion and simulated wind uplift criteria requirements.
 1. Fasteners are designed for the attachment of insulation and membrane to steel (18-24 gauge), wood, and structural concrete.
 2. Provide to meet FM requirements, fastener shall penetrate the steel deck 3/4 inch (19 mm). Minimum penetration is 1 inch (25 mm) in wood, 3/4 inch (19 mm) through wood that is less than 3/4 inch (19 mm) thick and 1-1/4 inches (32 mm) in concrete.

2.6 PRIMER

- A. Asphalt Primer: MuleHide A121 Asphalt Primer conforming to ASTM D41.
 1. Applied on all dissimilar materials except insulation.
 2. General purpose penetrating asphalt primer used to promote adhesion prior to the application of hot-mopped, cold-applied, and self-adhesive membrane systems as well as roof cements, mastics, and asphalt-based adhesives.
- B. SA Vertical Bond Contact Adhesive
 1. Low-VOC quick-drying, solvent-based, high-tack contact adhesive that is specifically



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

formulated to promote maximum adhesion of self-adhered membranes for applications in which adhesion is more challenging.

2.7 ASPHALT

- A. Certified in full compliance with requirements of Type III or IV asphalt listed in Table 1, ASTM D312. Each container, or bulk, shipping ticket shall indicate the equiviscous temperature (EVT), the finished blowing temperature (FBT), and the flash point.

2.8 MISCELLANEOUS

- A. Adhesive/Sealant:
1. MuleHide MH 241 Premium Modified flashing Cement. Meets or exceeds the requirements of ASTM D4586 Asphalt Roof Cement Type I.
 2. MuleHide MH 251 Premium Wet/Dry Elastomeric Flashing Cement. Meets or exceeds the requirements of ASTM D4586 Asphalt Roof Cement Type I.
 3. MuleHide MH 420 or MH 421 Modified Adhesive-Brush/Trowel Grade. Meets or exceeds the requirements of ASTM D3019 Type III Lap Adhesion.
- B. Insulation Adhesive:
1. Helix® or Helix® Max low-rise foam adhesive.

Helix® or Helix® Max Substrate Compatibility					
Insulation/Underlayments		Roof Decks		Existing Roofing Materials	
Poly ISO 1 & 2	Yes	Concrete	Yes	Smooth BUR	Yes
StructoDek® High Density	Yes	Cellular Lt.Wt. Concrete	Yes ¹⁰	Gravel BUR	Yes ⁵
Expanded Polystyrene (EPS)	Yes ¹	NVS Lt.Wt. Concrete	Yes ¹⁰	Mineral Cap Sheet	Yes
Extruded Polystyrene (XPS)	Yes ²	Gypsum	Yes	Granular Modified-Bitumen	Yes
New Sprayed Foam	No ⁸	Cementitious Wood Fiber	Yes	Smooth Modified-Bitumen	Yes
Scarified SPF	No ⁸	Plywood/OSB	Yes	Coal Tar Pitch	Yes ⁶
DensDeck®	Yes	Painted Steel	Yes	Aluminum-Coated BUR	No ⁷
Securock®	Yes	Galvanized Steel	Yes ³	Acrylic-Coated SPF	No ⁸
Oriented Strand Board	Yes	Acoustical Steel	Yes ⁴	Silicone-Coated SPF	No ⁸
Poly ISO 1-HD	Yes	Wood Plank	Yes	Unoxidized (Shiny) Asphalt	Yes ⁹

1. Standard EPDM (Non Fleece Back) membrane cannot be installed directly over EPS and requires a suitable overlayment or cover board.
2. For insulation attachment only, contact MuleHide Technical Department for options.
3. For new galvanized steel decks, power-washing is necessary to remove finishing oil residue if present.
4. For acoustical steel decks, fill the flutes with fiberglass or other suitable fill insulation and tack in place with strips of duct tape 3' OC, or other adhesive, prior to spraying the deck with Helix® Max Adhesive.
5. A minimum of an approved cover board or insulation is required over properly prepared gravel BUR.
6. An insulation providing the necessary R-value must be specified to prevent the coal tar pitch from softening.
7. Aluminum coatings must be removed by power-washing or by physical abrasion prior to the application of Helix® Max Adhesive. Adhesion tests are required to confirm sufficient preparation of the substrate.
8. SPF roofing assemblies may be considered on a job by job basis, contact Mule Hide Technical Department prior to bidding.
9. Requires AeroWeb for all applications.
10. Cellular or air-entrained lightweight substrates are acceptable. Lightweight concrete containing expanded aggregate such as perlite or vermiculite is not acceptable. New lightweight concrete must be confirmed by the contractor to be thoroughly dry. Existing substrates will require adhesion tests.

- C. Roofing Insulation: As specified in Section 07220.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

PART 3 EXECUTION

3.01 General

- A. The minimum application temperature for MuleHide SAMB materials is 40°F and rising for 48 consecutive hours.
 - 1. In order to perform properly, MuleHide SAMB materials require a minimum application temperature of 40°F and rising for 48 consecutive hours. This applies to the roofing materials and approved substrate. During installation, the membrane must be promptly rolled with a minimum 75# roller. Failure to abide by these requirements may result in poor adhesion or cracking issues.
 - 2. During periods of colder weather, the MuleHide SAMB materials should always be stored at room temperature (60°F to 80°F) until just prior to use. Materials that are not stored at room temperature (or not used within 4 hours) should be restored to room temperature prior to use.
- B. Application of the Helix® or Helix® Max Low-Rise Adhesive shall not proceed during periods of inclement weather. Follow MuleHide requirements for application temperatures and humidity levels.
- C. Do not apply Helix® or Helix® Max Adhesive when surface and/or ambient temperatures are below 25°F.

3.02 Substrate Conditions

The following general conditions apply to the substrate that will receive a MuleHide Self-Adhering Modified Bitumen Membrane Roofing System for both new construction and reroof applications:

- A. The roof deck must be structurally sound to provide proper securement for mechanical fasteners. Areas showing a loss of integrity due to corrosion, rotting, warping, concrete spalling, etc., must be repaired or replaced prior to installing the roofing system.
- B. It is the responsibility of the roofing contractor to perform test cuts at each roof area prior to reroofing. The condition of the substrate must be suitable to receive a MuleHide Self-Adhering Modified Bitumen Roofing System. Wet insulation must be removed and replaced. See Single-Ply Roofing Institute's guidelines for determining wet insulation.
- C. Contact the material manufacturer when the substrate is exposed to excessively high humidity and/or a corrosive environment. Special fasteners (e.g. stainless steel) or details may be required.
- D. A determination must be made regarding the presence or absence of coal tar pitch within the existing roof assembly when considering a recover of the old roof system. The presence of coal tar pitch requires the use of a 6-mil poly slipsheet under the new insulation unless the coal tar pitch is 10 years or older and is separated from the MuleHide Self Adhering Modified Bitumen membrane by a layer of insulation a minimum of 1-1/2" thick having a minimum "R" value of 5.0. All joints must be butted tightly together or have joints completely taped to prevent volatiles from damaging roof membrane.
- E. It is acceptable to install a MuleHide Self-Adhering Modified Bitumen Membrane Roofing System over the following deck substrates provided that an acceptable insulation is installed over the substrate as needed:
 - 1. **Structural Metal Deck** (22-gauge minimum) shall conform to recommendations outlined in Factory Mutual's Loss Prevention Data Sheet 1-28 (requires insulation). Contact MuleHide's Warranty Department for attachment requirements for decks less than 22-gauge in thickness. All FM testing is based on attachment to a 22-gauge steel deck.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

2. **Structural concrete and pre-cast, pre-stressed concrete** (2,500 psi minimum) shall be cured and dry to industry standards and surface shall be smooth and free of moisture or frost. All sharp ridges or other projections above the surface shall be removed before roofing. An approved insulation board is recommended. Minimum deck thickness shall be 2 inches with 3 inches preferred due to possible spalling damage that may occur to the underside of the deck when using fasteners for insulation and membrane attachment. Insulation may be attached with Type III or IV hot asphalt, approved adhesive or approved fasteners. The membrane may be adhered directly to structural concrete decks that have been trowel finished and are completely cured (28 day minimum). Gaps in the deck along the perimeter and around penetrations must be sealed along with vertical joints between tilt-up panels, if present, to prevent infiltration of hot humid air and possible moisture contamination resulting from condensation.
 3. **Lightweight Insulating Concrete** Fill and Metal Form Work (minimum 24-gauge) - the roof deck shall be cured and dry to the deck manufacturer's and/or industry standards and shall be smooth and free of ridges and depressions. All necessary venting as recommended by the roof deck manufacturer shall be accomplished. These decks may be acceptable to receive a MuleHide Self-Adhering Modified Bitumen Membrane Roofing System after pullout tests have been completed and appropriate fasteners have been selected. Attachment must be through the insulating concrete into the steel or light-weight concrete deck. Insulation board is required. Vapor barriers may be required when installing insulation over new decks.
 4. **Wood Plank (1" minimum)** shall conform to Factory Mutual's requirements for Class 1 impregnated decks (insulation is required). FM approved wood decks are a minimum, nominal 2-inch thick, tongue and groove planks. Wood Plank decks require the installation of MuleHide Nail Base mechanically attached to the deck prior to the installation of any self-adhering mod bit membrane. Nail Base may be substituted with the use of an approved rigid board insulation or cover board. MuleHide does not approve the direct adhesion to the wood deck with self-adhering modified bitumen membrane.
 5. **Plywood (15/32" minimum)** shall be exterior grade (minimum CDX grade). A layer of an approved insulation is required for reroof applications. On new construction, while insulation board is recommended, adhering directly to the plywood or Oriented Strand Board ("OSB") deck is acceptable if the decking is secured with screws or back-out resistant fasteners. Decks attached with common or cement coated nails or staples shall be covered with an approved insulation. Check with local building code requirements as adhering a Self-Adhering Modified Bitumen membrane direct to a wood deck may not meet local fire codes.
 6. **Cementitious Wood Fiber Decks** - Certain cementitious wood fiber decks may be acceptable to receive a MuleHide Self-Adhering Modified Bitumen Membrane Roofing System after pullout tests have been completed and appropriate fasteners have been selected. This deck type requires an acceptable insulation.
 7. **Gypsum Deck** - shall be cured and dry to manufacturers' and/or industry standards. The surface of the deck shall be smooth and free from ridges and depressions. Certain gypsum concrete decks may be acceptable to receive a MuleHide Self-Adhering Modified Bitumen Membrane Roofing System after pullout tests have been completed and appropriate attachment methods have been selected. This deck type typically requires an acceptable insulation.
 8. **Oriented Strand Board (OSB)** shall be a minimum 7/16" thick. Contact MuleHide for acceptable sheet sizes, fastener types and spacing when using OSB as requirements will change with thickness used. Minimum thickness or usage restrictions may change depending on local code requirements. Pullout tests must be performed and submitted to MuleHide Technical Department prior to bidding the project.
- F. MuleHide requires a minimum slope of 1/4" per foot, on certain deck types, such as plywood and structural concrete, the installation of insulation may be optional if the decks are properly sloped. Flat decks shall require tapered insulation systems to provide a minimum 1/4" per foot slope or greater. Structural concrete decks must have smooth trowel finish.
1. Application direct to structural concrete, aged wood (plywood, OSB), metal, metallic surfaces, smooth BUR, smooth Modified Bitumen and DensDeck Prime require the application of MuleHide #121 Asphalt



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

Primer prior to application of the SA Base Sheet, SA-SBS Cap Sheet, or SA-APP Cap Sheet. Primer must be allowed to dry thoroughly.

- G. MuleHide requires that all roof surfaces have a positive slope (Min 1/4" per foot) to provide adequate drainage. There should not be any ponding water 48 hours after a rainfall.
- H. For roof decks greater than 1-1/2" per foot the requirement of back nailing is required.
 - 1. Max 12" O.C on the cap sheet layer.
 - a. Metal nails are to be used for the back nailing

3.1 INSTALLATION

A. INSULATION INSTALLATION AND ATTACHMENT:

1. Incorrectly installed insulation can lead to roof system loss (blow-offs) and is the responsibility of the insulation installer, not the roof membrane manufacturer.
2. MuleHide does not warrant against improperly attached insulation or insulation failure caused by incorrect application.
3. All joints between layers should be staggered when multiple layers of insulation are installed.
4. Insulation shall be kept dry at all times. Install only as much insulation as can be covered with completed roofing membrane before the end of the day's work (or prior to onset of inclement weather).
5. Edges shall butt tightly, and all cuts shall fit neatly against adjoining surfaces to provide a smooth overall surface. Gaps of greater than 1/4" (6 mm) width shall be filled with insulation.
6. Install tapered insulation around roof drains and penetrations to provide adequate slope for proper drainage.
7. Mechanically attached insulation shall be fastened in accordance with Factory Mutual (FM) Approvals requirements for the applicable geographic Zone with the required number (and type) of fasteners and plates. Exception: where MuleHide requirements are more stringent than Factory Mutual (FM) Approvals, MuleHide requirements shall be followed.
8. When asphalt or foam adhesive attachment is selected by the project designer, the proposed insulation shall be compatible with the roof substrate, the proposed bitumen and the requirements of the specific MuleHide membrane. NOTE: Expanded polystyrene (EPS) materials shall not be installed with hot bitumen products.
9. Maximum 4' x 4' (1.2 m x 1.2 m) insulation boards can be attached with hot asphalt or foam adhesive.
10. Asphalt for insulation attachment shall meet ASTM D312 Type III or IV criteria, as dictated by the roof slope or other design conditions.

MuleHide's Minimum attachment rates shall be as follows:

Insulation Type or Overlay	Fasteners per 4' x 8' board		
	Field	Perimeter	Corner
Approved Polyisocyanurate - Min 2" thick (top layer)	8	12	16
Approved Polyisocyanurate - Min 1.5" up to 2" thick	12	18	24
Approved Polyisocyanurate - Min 1.0" up to 1.5" thick	16	24	32
1/2" HD Poly-ISO - Installed over Approved Insulation	16	24	32
HD Fiberboard - Min 1/2" thick- Installed over Approved Insulation	16	24	32
DensDeck Prime or Securock - Min 1/4" thick - Installed over Approved Insulation	12	18	24
OSB - Min 7/16" thick - Installed over Approved Insulation	17	25	32
Approved OSB/Polyisocyanurate Composite - Min 2" thick	17	25	32

Commence installation of the roofing system at the lowest point of the roof (or roof area), working up



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

the slope toward the highest point. Lap sheets shingle fashion so as to constantly shed water. For further information contact MuleHide Technical Services. Follow the recommendations for the specific type of material and layer as outlined below, or as specified. Type II standards, are acceptable for MuleHide roofing systems and should be appropriately installed in a manner approved for the specific product, e.g. fully adhered as self-adhered or with asphalt/or cold adhesive, heat-welded or mechanically attached (per industry standard fastening pattern) as applicable, and in accordance with specifications.

B. BASE AND PLY SHEET INSTALLATION:

1. Install in a manner approved for the specific product, e.g. fully adhered as self- adhered or mechanically attached.
2. Base or Inter-ply side laps are to be 3 inch (76 mm) minimum and usually delineated by a "lay line" for self adhered or mechanically attached application. End laps are typically 6 inches (152 mm) in all cases.
3. After adhering the sheet, it is required that uniform pressure be applied to the entire roll area by using a minimum 75# linoleum roller, water filled lawn roller or similar weighted roller. Care must be taken to prevent injury when rolling membrane, especially on sloped surfaces.
4. When completing end laps, cut the top corner of the top sheet on a 45-degree angle (start the cut approximately 3 inches in from the top edge and finishing down 3 inches from the top edge). Press the top sheet down and roll thoroughly with a silicone roller. When installing the next row of sheets, apply heat with a hot air welder along the cut edge till a slight bleed out and press down with a roller. If no welder, prior to pressing down the seam, apply a bead of MuleHide Mod Bit Sealant along the cut edge. This will seal any void along the cut edge when the next sheet is installed over the end lap. End laps should be staggered approximately min 3 feet apart.

A. CAP SHEET INSTALLATION:

1. MuleHide APP or SBS cap sheet membranes are intended to be used as the primary weathering surface in new and re-roof applications. MuleHide APP or SBS cap sheet membranes are to be applied as the uppermost layer of a multi-ply roof system over a compatible MuleHide base and/or interply sheet. MuleHide APP or SBS cap sheet membranes may be applied directly to approved substrates.
2. Apply over clean, dry, dust and debris-free substrates. Prime concrete decks and required substrates prior to application with MH 121 Fast-Drying Asphalt Primer. Consult MuleHide Technical Services if alternate primer is allowed.
3. When re-roofing, remove all prior roofing materials down to a clean, dust free substrate. Remove unused or abandoned through-roof penetrations.
4. All substrates shall be designed with proper expansion devices.
5. Wood decks shall have all joints cross blocked and/or properly supported.
6. Installation of the membrane should not adversely affect the ventilation of existing construction.
7. Do not apply directly to existing shingles or other unacceptable roof coverings.
8. While installing MuleHide APP or SBS cap sheet membranes:
 - a. Start at the lowest point of the roof.
 - b. Unroll the material and allow it to relax as membrane is positioned prior to installation.
 - c. Do not overheat to expose or compromise the reinforcement.
 - d. Position successive rolls using the 5" (13 cm) FASTLap at the end of the rolls, where applicable or at the granulated endlap. Bleed out of asphalt when heat welding the seam should be 1/8" –1/4" (3 mm–6 mm) (typical all seams).
 - e. Laps may be lightly rolled with a 4"–6" (10 cm–15 cm) wide roller to ensure lap is fused.
 - f. When completing end laps, cut the top corner of the top sheet on a 45-degree angle.
 - g. Details and flashings may be installed using heat-welding techniques. Do not adhere using cold adhesives or hot asphalt. Refer to manufacturer's published details for proper design and installation of detail work.
 - h. **Remember to thoroughly roll each sheet with a min 75# weighted roller as soon as the sheet is installed.**



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

B. ADHESIVE ATTACHMENT

1. Adhesive attachment substrate preparation
 - a. The surface to which adhesive is to be applied shall be dry, clean and free of fins, protrusions, sharp edges, loose and foreign materials, oil and grease. Depressions greater than 1/4" shall be filled with Helix® or Helix® Max Adhesive or other approved patching material. All sharp projections shall be removed. Previously unexposed (shiny) asphalt must be primed with AeroWeb.
 - b. Seal gaps between the wall/penetration and concrete deck with MuleHide F5 Air & Vapor Barrier, FROTH-PAK, or other suitable material, to avoid condensation issues and positive pressure from air infiltration.
 - c. Apply Helix® or Helix® Max Adhesive when the substrate and ambient temperatures are 25°F or above when spraying or extruding with heated or non-heated equipment. Dispense the adhesive between 300-800 psi depending on the equipment used. Consult MuleHide Technical Department for more details.
2. Adhesive installation
 - a. For spray applied applications, spray adhesive to obtain full coverage (approx. 1/8" to 1/4" thick after foaming).
 - b. For bead applications, apply adhesive at 4", 6", or 12" on center with a minimum 1/2" wide wet bead. For steel decks, bead attachment of Helix Max Adhesive must run parallel with and be on top of the steel deck flutes.

Bead Spacing Requirements				
Building Height	Perimeter Width	Bead Spacing		
		Field	Perimeter	Corner
0-25'	4 Feet	12" OC	6" OC	6" OC
26'-49'	8 Feet	12" OC	6" OC	6" OC
50'-74'	12 Feet	12" OC	6" OC	6" OC
75'-100'	16 Feet	12" OC	6" OC	6" OC
101' or greater	Contact MuleHide Technical Department			

3. Factory Mutual bead spacing guidelines in the perimeter and corner may differ from the table above. Beads at 12" OC are not acceptable at perimeters and corners.
4. Allow adhesive to rise and develop "string/body" (approx. 1.5 - 2 min.). String time will vary based on environmental conditions like temperature and humidity. Do not allow the adhesive to over-cure (lose tack) prior to setting insulation boards.
5. Place insulation boards (maximum 4' x 4'), or cover boards (DensDeck Prime or Securock may be 4' x 8') into adhesive after allowing it to rise and develop "string/body".
6. Designate one person to walk boards into place and then roll the boards between 5-7 minutes from the initial adhesive application. Boards may be temporarily weighted or relief-cut where necessary to keep the boards in constant contact with the adhesive until the adhesive cures.
7. At the beginning of the insulation attachment process and periodically throughout the day, check the adhesion of boards to ensure a tight bond is created and maximum contact is achieved.

CAUTION: Gaps between horizontal and vertical surfaces of the roof area as well as gaps around penetrations must be sealed to prevent interior warm air from infiltrating and condensing within the roofing assembly. Condensing moisture could weaken bottom insulation facer and eventually result in dislodgement or loose boards when adhesive is used.

NOTE: Projects utilizing MuleHide's F5 Air & Vapor Barrier must comply with MuleHide's installation requirements and published details.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

C. COLD WEATHER INSTALLATION

MuleHide advises against installing modified bitumen membranes at temperatures lower than 40°F–45°F (4°C–7°C) (wherever practicable). Where work is unavoidable at such temperatures, we recommend the following precautions be taken:

1. Take extra care during cold weather installation (Below ambient temperatures of 40°F–45°F (4°C–7°C), whereas ambient temperatures are affected by wind, humidity, etc.), to ensure adequate bonding is achieved between the surfaces to be joined. This applies to both material seam welds and adhesion of the applied product to the appropriately prepared substrate (substrate can be affected by such temperature constraints as well).
2. In addition, unrolling of cold materials, under very low ambient conditions must be avoided to prevent the likelihood of unnecessary stress cracking. The rolls must be at least 40°F (4°C) at the time of application. Should the membrane roll become stiff or difficult to install, it should be replaced with a new roll from the storage area.
3. To prevent the aforementioned situations and to ease the progress of installation under unfavorable conditions we recommend the following procedures:
 - a. The general recommendations of the National Roofing Contractors Association (NRCA) and Asphalt Roofing Manufacturers Association (ARMA) should be taken into account and will be helpful.
 - b. Remember that wind chill will have an effect on the application temperature.
 - c. Ensure that membrane is only installed to properly dry, clean and primed (where necessary) surfaces as required by the specifications.
 - d. Store membrane, until immediately prior to installing the roll. Minimum ambient temperature of the storage area should be 55°F–60°F (13°C– 15°C).
 - e. Once rolls of material are taken from the temperature controlled storage area, install before the temperature of the material drops below 40°F– 45°F (4°C–7°C).

D. VAPOR RETARDERS

1. Adequate moisture vapor control is recommended (when appropriate) as a lack thereof may result in the accumulation of moisture in the roofing assembly.
2. An analysis of dew point and vapor flow should be assessed during an initial project design for the building as well as for re-roofing and re-cover applications as they can alter existing vapor flow.
3. In general, vapor retarders may be required when high interior relative humidity is present. The condition is typically seen with food processing facilities, swimming pools, paper mills, laundry facilities, etc.
4. Vapor retarders are sometimes referred to as temporary or secondary roofs.
5. The necessity for use of a vapor retarder is the responsibility of the design professional and should be reviewed and approved by the building owner. The type, location and method of application is also to be determined by the design professional.
6. The National Roofing Contractors Association (NRCA) as well as the American Society of Heating, Refrigerating and Air Conditioning Engineers (ASHRAE) may be referenced for recommendations on the necessity of a vapor retarder.

E. SPECIAL APPLICATIONS

1. MuleHide roofing assemblies are sometimes selected for installation over buildings that include unique environments and are deemed special purpose.
2. These would include cold storage facilities, pools, as well as partially enclosed and open buildings such as hangars.
3. These should be carefully reviewed as they pose design and building conditions such as elevated moisture or humidity, unusually elevated or lowered temperatures, and elevated pressure conditions.
4. Special applications also include overburden or plaza deck assemblies. These typically include



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

- the addition of additional materials for protection of the newly installed roof.
5. MuleHide Technical Services should be contacted prior to these installations.

F. DRAINAGE

1. Adequate drainage is required for a well-functioning low-slope roof system. The minimum required slope is 1/4" (6 mm) per foot.
2. Absence of proper drainage often results in "Ponding". It is defined by the National Roofing Contractors Association (NRCA) as water that has not dissipated from the roof within 48 hours.
3. Ponding water negatively affects the membrane and can result in premature deterioration, and is not covered by MuleHide warranties.
4. The ideal structural roof deck is designed to provide adequate slope and drainage. When the roof deck has not been constructed to provide proper slope and drainage, the use of tapered insulation is required.
5. Primary and secondary drains shall be of sufficient number and diameter and located so as to provide adequate drainage of the entire roof surface.
6. The adequacy of drainage provisions, placement, sizing and/or number of drains required is the responsibility of the design professional. Drainage conditions should meet the requirements of codes as well as standard industry recommendations.

G. CANTS

1. Cant Strips are required at all horizontal/vertical intersections. They may be mechanically fastened or adhered to the substrate depending upon the deck type.
2. Material type of Cant strip is dependent upon the application method of the roofing assembly. Hot asphalt applied systems may utilize Perlite (conforming to ASTM C728) or wood fiber (conforming to ASTM C209). Heat welded flashing assemblies require the use of Perlite only. Self-Adhered flashing applications are recommended to include wood Cant strip (primed).

H. WOOD NAILERS

1. It should be noted that both wood nailers and blocking materials are deemed as a component of the structure – not the roofing assembly. However, wood nailers are critical to the success of a well-performing roof.
2. Care for selection of proper lumber used for nailers is important to ensure the selection of the appropriate type and level of corrosion resistance for fasteners.
3. All nailers should be installed as per Factory Mutual (FM) LPDS 1-49 "Perimeter Flashing".
4. ANSI/SPRI ES-1 should also be referenced for edge metal and parapet wall top conditions to ensure the installation of the nailer materials/attachment to resist calculated wind loads.

I. EXPANSION JOINTS/AREA DIVIDERS

1. Expansion joints are part of the building; considerations such as design and location must be taken at the time of original building design by design professionals and reviewed by the building owner. The purpose of the expansion joint is to minimize stress on the building from movement.
2. Per typical flashing details, expansion joints must be extended a minimum of 8" (20 cm) above the roof surface on curbs. Sheet metal caps or flexible expansion joint covers are used at the top surface of the expansion joint.
3. Expansion joints must be located so the typical drainage flow is not blocked.
4. Expansion joints are continuous along the break in the structure. They shall not be terminated short of the end of the roof deck.

J. AREA DIVIDERS

1. Area dividers can be similar to but are not considered expansion joints.
2. Typical uses for dividers are to section off roof sections which were not included in original



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

building design/construction. They can relieve stresses in an existing roofing system and can serve as a separator between two dissimilar roofing materials.

3. Area dividers are typically capped with a coping cap style sheet metal detail.

K. MEMBRANE FLASHINGS

1. Membrane flashings and their locations are particularly volatile and are most susceptible to moisture penetration. Proper installation at these locations is critical to the integrity of the roofing assembly.
2. Flashings, or, "Base Flashing", are locations on the roof whereby the field of the roof (horizontal surface) intersects with a wall, curb, penetrations (vertical surfaces), etc.
3. Membrane flashings entail the installation of two (2) plies of membrane at flashing locations. The products associated with the flashings may utilize same plies used for the overall roofing assembly.
4. Flashing locations that include irregularly shaped penetrations, low flashing clearance heights, or items too close to be properly flashed with membrane may be treated with Liqui-Flash. Contact MuleHide Technical Services for more information.
5. Minimum flashing height is 8" (20 cm) and the maximum flashing height is 24" (61 cm).
 - a. **The use of SA Vertical contact bonding adhesive to promote better adhesion is recommended for any vertical walls.**
6. Base flashings shall be mechanically fastened at the top edge and terminated with a proper termination bar and counterflashing.

L. WALKWAYS AND PROTECTED MEMBRANES

1. Walkways help protect the membrane from damage due to routine rooftop service traffic. Walkways may consist of an additional layer of similar MuleHide membrane of a contrasting color granulated surface, or another approved walkway system. The following are typical roof locations that utilize walkways:
 - a. All roof access points (ladders, hatches, doorways, etc.).
 - b. Areas subjected to traffic in excess of one monthly visit.
 - c. Areas with high pedestrian traffic or subject to frequent maintenance operations.
 - d. In addition to typical locations requiring walkways, the walkway material may also be applied beneath rooftop equipment such as blocking to support gas/plumbing lines, and small non curb mounted HVAC (or other) equipment placed on wood sleepers.

M. TEMPORARY TIE-INS

1. Install temporary cutoffs around incomplete edges of roofing assembly at the end of each day's work and when work must be postponed due to inclement weather. Temporary tie-ins shall be positioned so any sealed membrane edge will not buck or pond water. Ensure drainage is not restricted.
2. Remove all gravel, dirt, debris or other contaminants from the tie-in area and make sure all surfaces are clean and dry.
3. All loose membrane edges should be sealed downslope with products compatible with the existing substrate and membrane type being installed. Provide continuous pressure along the sealed edge to prevent water migration under the finished roof sections.
4. When work resumes, remove the temporary seals completely including contaminated membrane, sealants, insulation fillers, etc. from the work area and properly dispose.

Note: MuleHide does not warrant or guarantee the water tightness of any nightly tie-in. Temporary night seals and their performance are the sole responsibility of the roofing contractor.



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

N. SAFETY AND HEALTH

1. Strict Safety and Health precautions are necessary at all times. PLEASE READ, UNDERSTAND AND FOLLOW ALL INSTRUCTIONS ON LABELS AND PACKAGING AS WELL AS ANY APPLICABLE INDUSTRY

STANDARDS AND REGULATIONS. See also all relevant sections above. All volatile, or potentially volatile, materials such as primers, gas, cleaners, etc., shall be kept away from all ignition sources (e.g. flames, torches, fire, sparks, etc.). Consult product container labels and Safety Data Sheets for specific safety instructions. The application of those products installed with hot asphalt or torch may result in burns and other physical injury. Surfaces which contact the melted bitumen or torch may ignite. The installer should take utmost care when using hot materials such as asphalt or when heat-welding any product. This is especially important when there may be a danger of contact with materials which may smolder, such as cellulose and wood materials, wood fiber, etc. or flammable or highly flammable solvents or chemicals. MuleHide membranes may present a slip and fall hazard. This risk is increased when wet or icy conditions exist. Adequate precautions should be taken when working. Manufacturer recommends the use of OSHA approved fall protection for project conditions.

A. LIMITATIONS

1. MuleHide membranes should never be applied directly to TPO, EPDM, PVC, or other single ply membranes.
2. MuleHide Cold Applied membranes are not to be used with organic saturated felts.
3. Not to be installed over or under polystyrene insulation.

- B. Surface Coatings: Apply roof coatings in strict conformance with the specific manufacturer's recommended procedures.

3.2 Provide any corrections to bring the roofing installation into conformance with MuleHide requirements.

3.3 FIELD QUALITY CONTROL

- A. Inspection: Manufacturer shall conduct field observations as deemed necessary by MuleHide for projects requiring MuleHide Roofing Systems Warranty. The number and frequency of field observations shall be as required by MuleHide Technical Services Department.
- B. Contractor shall correct any deficiencies observed by MuleHide Technical Services to bring the roofing installation into specification conformance with MuleHide warranty requirements.

3.4 CLEANING

- A. Clean-up and remove daily from the site all wrappings, empty containers, paper, loose particles and other debris resulting from these operations.
- B. Remove asphalt markings from finished surfaces.
- C. Repair or replace defaced or disfigured finishes caused by Work of this section.

3.5 PROTECTION

- A. Provide traffic ways, erect barriers, fences, guards, rails, enclosures, chutes and the like to protect personnel, roofs and structures, vehicles and utilities.
- B. Protect exposed surfaces of finished walls with tarps to prevent damage.
- C. Plywood for traffic ways required for material movement over existing roofs shall be not less than 5/8



System Specifications

Self-Adhering Modified Bitumen Membrane Systems

June 2026

inch (16 mm) thick.

- D. In addition to the plywood listed above, an underlayment of minimum 1/2 inch (13 mm) recover board is required on new roofing.
- E. Special permission shall be obtained from MuleHide before any traffic shall be permitted over new roofing.

END OF SECTION