



ICC
EVALUATION
SERVICE

In Cooperation with



Most Widely Accepted and Trusted

ICC-ES Evaluation Report

ICC-ES | (800) 423-6587 | (562) 699-0543 | www.icc-es.org

ESR-1184

Reissued 03/2019

This report is subject to renewal 03/2021.

DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION
SECTION: 07 53 23—ETHYLENE-PROPYLENE-DIENE-MONOMER ROOFING
SECTION: 07 54 23—THERMOPLASTIC-POLYOLEFIN ROOFING

REPORT HOLDER:

CARLISLE SYNTEC SYSTEMS

EVALUATION SUBJECT:

CARLISLE BALLASTED SINGLE-PLY ROOFING SYSTEMS MEMBRANES—EPDM AND TPO



“2014 Recipient of Prestigious Western States Seismic Policy Council (WSSPC) Award in Excellence”



ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.



Copyright © 2019 ICC Evaluation Service, LLC. All rights reserved.

ICC-ES Evaluation Report

ESR-1184

Reissued March 2019

This report is subject to renewal March 2021.

www.icc-es.org | (800) 423-6587 | (562) 699-0543

A Subsidiary of the International Code Council®

DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION
Section: 07 53 23—Ethylene-Propylene-Diene-Monomer Roofing
Section: 07 54 23—Thermoplastic-Polyolefin Roofing

REPORT HOLDER:

CARLISLE SYNTEC SYSTEMS

EVALUATION SUBJECT:

CARLISLE BALLASTED SINGLE-PLY ROOFING SYSTEMS MEMBRANES—EPDM AND TPO

ADDITIONAL LISTEES:

VERSICO

WEATHERBOND

MULE-HIDE PRODUCTS COMPANY, INCORPORATED

ROOFING PRODUCTS INTERNATIONAL, INC.

1.0 EVALUATION SCOPE

Compliance with the following code:

- 2018, 2015, 2012 and 2009 *International Building Code*® (IBC)
- 2018, 2015, 2012 and 2009 *International Residential Code*® (IRC)
- 2013 *Abu Dhabi International Building Code*® (ADIBC)[†]

[†] The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

Properties evaluated:

- Weather resistance
- Fire classification
- Wind uplift resistance
- Impact resistance

2.0 USES

The Carlisle ethylene propylene diene monomer (EPDM) and thermoplastic polyolefin (TPO) single-ply membranes are used in ballasted single-ply membrane roofing systems.

3.0 DESCRIPTION

3.1 General:

The Carlisle Ballasted Single-ply Membrane Roofing

System consists of single-ply EPDM or TPO membranes, insulation where used, flashing, ballast, splicing cement and splice tape that are installed on a combustible or noncombustible deck.

Information in this report pertaining to the Carlisle Ballasted Roofing System is also applicable to the Versico, WeatherBond, Mule-Hide and Roofing Products International, Inc. Ballasted Roofing Systems. See Table 1 for corresponding product names.

3.2 Single-ply Membranes:

3.2.1 EPDM Membrane: The Carlisle Sure-Seal and Sure-Tough EPDM membranes are reinforced or nonreinforced roof coverings available in thicknesses ranging from 45 mils (0.045 inch [1.14 mm]) to 90 mils (0.090 inch [2.29 mm]).

3.2.2 TPO Membrane: The Carlisle Sure-Weld membranes consists of a polyester reinforcement encapsulated between two layers of TPO and is available in thicknesses ranging from 45 mils (0.045 inch [1.14 mm]) to 80 mils (0.080 inch [2.03 mm]).

3.3 Insulation:

See Table 2 for insulations for use with specific roofing systems. Foam plastic insulation, where used, must have a flame-spread index of not more than 75 when tested at the maximum thickness intended for use in accordance with ASTM E84.

3.4 Flashing:

Flashing must be provided in accordance with Section 1503.2 of the IBC. Where flashing is of metal, the metal must be corrosion-resistant, minimum No. 26 gage [base-metal thickness 0.019 inch (0.483 mm)] galvanized steel.

3.5 Ballast:

Ballast must be provided in accordance with IBC Section 1504.8 and ANSI/SPRI RP-4. Nominally 1½-inch or 2½-inch smooth river bottom stone must be as specified in ASTM D448. Pavers may be substituted in accordance with ANSI/SPRI RP-4.

3.6 Splicing Cement, Tape or Welding:

3.6.1 Sure-Seal EP-95 Splicing Cement: Sure-Seal EP-95 Splicing Cement is a high-strength, solvent-based contact cement used for seaming EPDM membranes together. The splicing cement is supplied in 1-gallon (3.78 L) cans and has a shelf life of one year.

3.6.2 Sure-Seal SecurTAPE: Sure-Seal SecurTAPE is a pressure-sensitive splice tape used for seaming EPDM membranes together. The splice tape is supplied in cartons of two or four rolls each and has a shelf life of one year.

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.



3.6.3 Welding: Adjoining sheets of Sure-Weld TPO membrane are overlapped and joined together with a minimum 1½-inch-wide heat weld.

3.7 Impact Resistance:

The EPDM and TPO roofing membranes described in this report meet requirements for impact resistance in Section 1504.7 of the IBC, based on testing in accordance with FM 4470.

4.0 DESIGN AND INSTALLATION

4.1 General:

Installation of the Carlisle ballasted EPDM and TPO membrane roofing systems must comply with the applicable code, the manufacturer's published installation instructions and this report. The manufacturer's published installation instructions must be available at all times on the jobsite during installation. Typical installation details are shown in Figure 1.

The slope of the roof on which the Carlisle single-ply membranes are installed must be a minimum of 1/4:12 (2 percent slope) and must not be more than 2:12 (17 percent slope).

Penetrations and terminations of the roof covering must be flashed and made weather-tight in accordance with the requirements of the membrane manufacturer and the applicable code.

4.2 Fire Classification:

Carlisle ballasted single-ply membrane roofing systems installed in accordance with this report are classified as Class A roof coverings as noted in Table 2.

4.3 Wind Uplift Resistance:

The Carlisle ballasted single-ply membrane roofing systems must be designed for wind resistance in accordance with ANSI/SPRI RP-4 Wind Design Guide and IBC Section 1504.8.

Metal edge securement for roofing systems must be listed in accordance with ANSI/SPRI ES-1 and designed and installed for wind loads in accordance with IBC Section 1504.5 and IBC Chapter 16.

4.4 Reroofing:

The existing deck must be inspected to verify that the structure to be reroofed is structurally sound and adequate to support and secure the roofing membrane. Prior to installation of new roof coverings, inspection by and written approval from the code official having jurisdiction must be required.

The Carlisle EPDM and TPO ballasted roof covering systems described in Table 2 are classified as Class A roof assemblies when installed over existing classified roof assemblies.

5.0 CONDITIONS OF USE

The EPDM and TPO membranes described in this report comply with, or are suitable alternatives to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

5.1 Installation must comply with the applicable code, the manufacturer's published installation instructions and this report. The instructions within this report must govern if there are any conflicts between the manufacturer's instructions and this report.

5.2 The Carlisle Ballasted Single-Ply Membrane Roofing

Systems must be installed by professional roofing contractors trained and approved by the manufacturer.

5.3 Foam plastic insulation must be separated from the interior of the building by an approved thermal barrier in accordance with IBC Section 2603.4.

5.4 Foam plastic insulation, where used, must bear the label of an approved agency indicating that the foam plastic has a flame-spread index of not more than 75 when tested in accordance with ASTM E84 at the maximum thickness intended for use, subject to the approval of the code official.

5.5 The ballasted roofing system must be designed for wind resistance in accordance with the ANSI/SPRI RP-4 Wind Design Guide for Ballasted Single-Ply Roofing Systems. Design drawings must be prepared, signed and sealed by a registered design professional where required by the statutes of the jurisdiction in which the project is to be constructed, and submitted to the code official for approval.

5.6 Design wind uplift pressure on any roof area, including edge and corner zones, must not exceed the allowable wind-uplift pressure for the system installed in that particular area.

5.7 The structural roof system to which the ballasted membrane is to be applied must be certified as being capable of sustaining the construction, membrane, ballast, and ancillary material loads that will be encountered during and subsequent to membrane application. This certification must be provided by a registered design professional.

5.8 The membranes are manufactured at Carlisle, Pennsylvania; Greenville, Illinois; Senatobia, Mississippi; and Tooele, Utah, under a quality control program with inspections by ICC-ES.

5.9 For buildings under the IBC, above-deck thermal insulation board must comply with the applicable standards listed in Table 1508.2 of the IBC.

6.0 EVIDENCE SUBMITTED

Data in accordance with the ICC-ES Acceptance Criteria for Membrane Roof Covering Systems (AC75), dated July 2010 (Editorially revised March 2018).

7.0 IDENTIFICATION

7.1 Each roll or package of rolls of EPDM and TPO membrane must bear a label noting the product name, the report holder's name (Carlisle SynTec) or the name of the additional listee (Versico, WeatherBond, Mule-Hide Products Company, Incorporated or Roofing Products International, Inc.), the manufacturer's address or plant code, and the evaluation report number (ESR-1184) when used in a ballasted roof system. The roof membranes shown in Table 1 shall be recognized in accordance with evaluation report number ESR-1463 when used in a non-ballasted roof system. Product labels may contain both evaluation report numbers.

7.2 The report holder's contact information is the following:

CARLISLE SYNTEC SYSTEMS
POST OFFICE BOX 7000
CARLISLE, PENNSYLVANIA 17013
(717) 245-7000
www.carlislesyntec.com

7.3 The Additional Listees' contact information is the following:

VERSICO
POST OFFICE BOX 1289
CARLISLE, PENNSYLVANIA 17013

WEATHERBOND
POST OFFICE BOX 251
PLAINFIELD, PENNSYLVANIA 17081

MULE-HIDE PRODUCTS COMPANY, INCORPORATED
1195 PRINCE HALL DRIVE
BELOIT, WISCONSIN 53511

ROOFING PRODUCTS INTERNATIONAL, INC.
57460 DEWITT STREET
ELKHART, INDIANA 46517

TABLE 1—CORRESPONDING ROOF COVERING PRODUCT NAMES

CARLISLE PRODUCT NAME	VERSICO PRODUCT NAME	WEATHERBOND PRODUCT NAME	MULE-HIDE PRODUCT NAME	ROOFING PRODUCT INTERNATIONAL PRODUCT NAME
Sure-Seal	VersiGard Non-Reinforced EPDM	WeatherBond EPDM Non-Reinforced	Mule-Hide Standard Black EPDM	Royal Edge Non-Reinforced EPDM
Sure-Seal FR	VersiGard FR Non-Reinforced EPDM Membrane	WeatherBond FR EPDM Non-Reinforced	Mule-Hide FR EPDM	Royal Edge Non-Reinforced FR EPDM
Sure-Seal FleeceBACK	VersiFleece EPDM	WeatherBond EPDM Fleece	-	Royal Edge EPDM FleeceBACK
Sure-Seal AFX	VersiFleece AC EPDM	WeatherBond AC EPDM Fleece	-	-
Sure-Tough	VersiGard Reinforced EPDM	WeatherBond Standard Reinforced EPDM	Mule-Hide Standard Reinforced EPDM	Royal Edge reinforced EPDM
Sure-Tough FR	VersiGard FR Reinforced EPDM	WeatherBond FR Reinforced EPDM	Mule-Hide FR Reinforced EPDM	Royal Edge Reinforced Fire Rated EPDM
Sure-White	VersiGard White Standard	WeatherBond White EPDM	Mule-Hide White-on-Black EPDM	Re-Flex White EPDM
Sure-White FleeceBACK	-	-	-	Re-Flex White EPDM FleeceBACK
Sure-Weld	VersiWeld Reinforced TPO	WeatherBond TPO	Mule-Hide TPO-c	Re-Flex TPO
Sure-Weld HS	VersiWeld HS/ES	WeatherBond High Slope TPO	Mule-Hide TPO-c FR	Re-Flex TPO HS
Sure-Weld FleeceBACK	VersiFleece TPO	WeatherBond TPO Fleece	Mule-Hide TPO-c Fleece Back	Re-Flex TPO FleeceBACK
Sure-Weld AFX	VersiFleece AC TPO	WeatherBond TPO AC Fleece	Mule-Hide TPO-c Fleece Back Plus	-
EP-95 Splicing Cement	Splice Adhesive	Splice Adhesive	Mule-Hide Splice Adhesive	Royal Edge Splice Adhesive
SecurTAPE	Quick-Applied Seam Tape	WeatherBond Peel & Stick Seam Tape	Mule-Hide EPDM In-Seam Tape	Royal Edge Seam Tape

¹These products are recognized in Table 1 may also be used in non-ballasted roof systems when installed in accordance with ESR-1463. For additional details regarding product specifications and identification, see ESR-1463.

TABLE 2—FIRE CLASSIFICATION ASSEMBLIES—BALLASTED ROOFING SYSTEMS¹

SYSTEM NO.	ROOF CLASS	ROOF DECK	MAXIMUM ROOF SLOPE	INSULATION ^{1,2}	COVER BOARD	MEMBRANE ¹
1	A	Combustible or Noncombustible	2:12	Any UL classified insulation, any thickness, any combination	-	EPDM or TPO membrane

For SI: 1inch = 25.4 mm.

¹Insulation and membrane are laid loosely and surfaced with river-bottom stones, nominally 1½ inches in diameter, at 1000 lbs. per square (min.). Suitable alternates are size Nos. 1, 2, 3, 4 and 24 (as per ASTM D448), also at 1000 lbs/sq min. In addition, concrete pavers or crushed stone may be used. Pavers must weight 1000 lbs/sq min and spaced no more than 1/8 in. apart and the crushed stone must meet the above size and weight requirements.

²All foam plastic insulation must be UL-classified foamed plastic for roofing systems, and must conform to ASTM C578 or ASTM C1289 specifications.




FIGURE 1